

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : A61K 47/48, A61L 27/00	A2	(11) International Publication Number: WO 99/47176 (43) International Publication Date: 23 September 1999 (23.09.99)
(21) International Application Number: PCT/US99/05245 (22) International Filing Date: 11 March 1999 (11.03.99) (30) Priority Data: 60/078,383 18 March 1998 (18.03.98) US 09/177,318 22 October 1998 (22.10.98) US (71) Applicant: SURMODICS, INC. [US/US]; 9924 West 74th Street, Eden Prairie, MN 55344 (US). (72) Inventors: GUIRE, Patrick, E.; 6741 Tartan Curve, Eden Prairie, MN 55346 (US). ANDERSON, Aron, B.; 4847 Birchwood Lane, Minnetonka, MN 55343 (US). AMOS, Richard, A.; 3437 Skycroft Circle, St. Anthony, MN 55418 (US). EVERSON, Terrence, P.; 560 Country Court, Eagan, MN 55123 (US). (74) Agents: GOLDMAN, Philip, M. et al.; Fredrikson & Byron, P.A., 1100 International Centre, 900 2nd Avenue South, Minneapolis, MN 55402-3397 (US).		(81) Designated States: AU, CA, JP, MX, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>Without international search report and to be republished upon receipt of that report.</i>
(54) Title: LATENT REACTIVE BLOOD COMPATIBLE AGENTS (57) Abstract <p>A reagent and related method for use in passivating a biomaterial surface, the reagent including a latent reactive group and a bifunctional aliphatic acid (e.g., fatty acid), in combination with a spacer group linking the latent reactive group to the aliphatic acid in a manner that preserves the desired function of each group. Once bound to the surface, via the latent reactive group, the reagent presents the aliphatic acid to the physiological environment, <i>in vivo</i>, in a manner (e.g., concentration and orientation) sufficient to hold and orient albumin.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

LATENT REACTIVE BLOOD COMPATIBLE AGENTS

CROSS REFERENCE TO RELATED APPLICATIONS

5 The present application is a continuation of US patent application filed October 22, 1998 and assigned Serial No. 09/177,318, which is a continuation of provisional US patent application filed March 18, 1998 and assigned Serial No. 60/078,383, the entire disclosure of which is incorporated herein by reference.

TECHNICAL FIELD

10 The present invention relates to reagents and methods for rendering a surface biocompatible, and in particular to reagents and methods for "passivating" the surface of an implantable medical device in order to render it hemocompatible. In another aspect, the invention relates to biomedical devices, *per se*, and in particular those
15 having biocompatible, including hemocompatible, tissue-contacting surfaces.

BACKGROUND OF THE INVENTION

Manufacturers of implantable medical devices have long attempted to understand, and in turn improve, the performance of materials used in blood-contacting applications (Leonard, E.F., et al. Ann. N.Y. Acad. Sci. 516, New York, Acad. Sci.,
20 New York, 1987). The biological response of the body, as well as problems with infection, have hindered the application of implantable, disposable, and extracorporeal devices. Anticoagulant drugs, such as heparin and coumadin, can improve the use of such devices, although anticoagulants have their own corresponding risks and
25 drawbacks. For these reasons, development of materials having greater compatibility with blood has been pursued aggressively (Sevastianov, V.I., CRC Crit. Rev. Biocomp. 4:109, 1988).

Two general strategies that have been used to develop improved blood-contacting materials include modifying the chemistry of the bulk material itself, and/or
30 modifying the interfacial properties of the material. With regard to the latter approach, several classes of materials have been covalently bonded onto blood-contacting surfaces with the goal of improving blood compatibility. These include anticoagulants, such as

heparin and hirudin; hydrogels; polyethylene oxide (PEO); albumin binding agents; cell membrane components; prostaglandins; and sulfonated polymers. These approaches have met with varying degrees of success in terms of reducing protein adsorption, platelet adhesion and activation, and thrombus formation. Unfortunately, no approach
5 has yet been shown to be universally applicable for improving blood-biomaterial interactions.

As mentioned above, albumin binding agents have been considered for use on biomaterials. Biomaterials having a high surface concentration of albumin have been shown to be less likely to initiate the fibrin cascade and platelet attachment than those
10 having a high concentration of other serum proteins, such as fibrinogen, fibronectin, or immunoglobulins. On many polymeric materials, however, fibrinogen is often the predominant protein adsorbed from protein mixtures or plasma. For these reasons, investigators have attempted to immobilize albumin onto materials or to design biomaterial surfaces that will enhance binding of endogenous albumin from blood, thus
15 mitigating the adsorption of fibrinogen and consequent thrombogenic phenomena.

In this respect, a number of different approaches have been employed to date. These approaches include passive adsorption or covalent immobilization of albumin to the surface, and the development of surfaces designed to selectively bind endogenous albumin from circulating blood, the latter using alkyl chain-modified materials and other
20 means.

Munro, et al., U.S. Patent No. 4,530,974, discloses a method of adsorbing albumin to a water-insoluble polymer such as polyurethane by covalently binding to the surface a nonionic hydrophobic aliphatic chain to which serum albumin will selectively bind.

25 Frautschi et al., U.S. Patent No. 5,017,670 and U.S. Patent No. 5,098,977, teach methods for covalent attachment of aliphatic extensions of 12 to 22 carbon atoms to water-insoluble polymers containing aromatic rings and ring structures with adjacent secondary hydroxyls for increased albumin binding.

Eaton, U.S. Patent No. 5,073,171, describes a biocompatible prosthetic device
30 incorporating an amount of an albumin binding dye effective to form a coating of

endogenous albumin on the device when the device is in contact with a physiological fluid containing albumin.

While some or all of these various strategies can be used to enhance the binding of endogenous albumin to blood-contacting material surfaces, and in turn to reduce fibrinogen binding, these approaches are each limited in one or more respects. Alkyl chain-modified surfaces have been shown to increase albumin binding and decrease fibrinogen binding, but these effects were fairly limited, for instance, to a short term time frame (generally less than one hour). In addition, various other surface modification methods discussed above are useful for only a narrow range of substrate materials.

On another subject, the assignee of this application has developed the ability to attach bioactive groups to a surface by covalently bonding those groups, directly or indirectly, to the surface. For instance, US Patent Nos. 4,722,906, 4,979,959, 4,973,493 and 5,263,992 relate to devices having biocompatible agents covalently bound via photoreactive groups and a chemical linking moiety to the biomaterial surface. US Patent Nos. 5,258,041 and 5,217,492 relate to the attachment of biomolecules to a surface through the use of long chain chemical spacers. US Patent Nos. 5,002,582 and 5,512,329 relate to the preparation and use of polymeric surfaces, wherein polymeric agents providing desirable properties are covalently bound via a photoreactive moiety to the surface. In particular, the polymers themselves exhibit the desired characteristics, and in the preferred embodiment, are substantially free of other (e.g., bioactive) groups.

It would be highly desirable to be able to attach albumin to a biomaterial surface in a manner that is suitably stable for extended use, particularly in a manner that permits the albumin to be replenished over time and in the course of use.

SUMMARY OF THE INVENTION

The present invention provides a novel reagent for use in passivating a biomaterial surface, the reagent comprising a latent reactive group and a bifunctional aliphatic acid, in combination with a spacer group linking the latent reactive group to the aliphatic acid in a manner that preserves the desired function of each group. The reagent can be used to passivate a surface by activating the latent reactive group in the

presence of the surface in order to covalently bond the reagent to the surface. Once bound to the surface, the reagent presents the aliphatic acid to the physiological environment, *in vivo*, in a manner (e.g., concentration and orientation) sufficient to hold and orient albumin. Preferably, over time, the reagent surface is able to replenish
5 itself by replacing albumin molecules that have become unbound or deteriorated with new albumin molecules. Albumin (e.g., human serum albumin (HSA)), is defined as any naturally occurring proteinaceous moiety containing a fatty acid binding site.

In a preferred embodiment, the reagent is of the general formula $(X)_m-Y-(Z)_n$ where X is a latent reactive (e.g., photoreactive) group, Y is a spacer radical, and Z is
10 a bifunctional aliphatic acid, as each are described herein. The values of m and n are ≥ 1 and while m can equal n, it is not necessary. The aliphatic acid is 'bifunctional' in that it provides both an aliphatic region and an anionic (e.g., carboxylic acid) region. Once attached to a surface, these portions cooperate in the process of attracting and binding of albumin in order to passivate the surface.

15 In the preferred embodiment where both m and n = 1, the reagent is termed a heterobifunctional reagent. The aliphatic acid is preferably attached to the latent reactive group by means of a divalent spacer group in a manner that does not detrimentally affect the function of either the aliphatic or anionic portions. Higher-valent spacer groups can also be selected which permit the attachment of multiple
20 aliphatic acid and latent reactive groups, again in a manner which does not detrimentally affect the functions of the respective groups. In this case m does not necessarily equal n and both are ≥ 1 .

In a further embodiment, the spacer group can be a multivalent polymer having multiple sites along the backbone which permit covalent attachment of the
25 aliphatic acid and latent reactive groups. These groups can be attached to a preformed reactive polymer using conventional chemical coupling techniques or may be incorporated during the polymerization process by use of appropriately substituted monomers. In this embodiment, m does not necessarily equal n and typically both are larger than one.

The invention further provides a method for preparing a passivating reagent, as well as a method of using the reagent to passivate the surface of a synthetic or natural biomaterial. In yet a further embodiment, the invention provides a surface coated with a passivating reagent of this invention, and in turn, an article fabricated from a material providing a surface coated or coatable with such a reagent. In yet a further embodiment, the invention provides a passivated biomaterial surface having reagent attached thereto and albumin attracted and attached to the bound reagent.

DETAILED DESCRIPTION

The present invention permits the binding of albumin to a surface to be enhanced by the use of a surface modification reagent. The reagent includes a bifunctional aliphatic acid capable of being attached to a surface in an amount and orientation that improves the ability of the surface to attract and bind albumin. While not intending to be bound by theory, it appears that a surface bearing a reagent of this invention exhibits improved albumin binding by virtue of both hydrophobic interactions (of the alkyl chain) and ionic interactions (of the anionic moiety) with albumin. It is expected that the hydrophobic interactions serve to hold and orient the free albumin molecule, while the ionic interactions serve to maintain the albumin molecule in position by the addition of attractive ionic forces. In a particularly preferred embodiment, the bifunctional aliphatic acid is attached to either alkane, oxyalkane, or hydrophobic polymeric backbones to allow both aliphatic and ionic regions of the bifunctional acid analog to spacially orient away from the biomaterial surface to induce better binding with native albumin. The reagent, in turn, permits albumin binding surfaces to be created using a variety of medical device materials, and in particular, for use in blood-contacting medical devices.

Bifunctional Aliphatic Acid

The bifunctional aliphatic acid of the present invention ("Z" group) includes both an aliphatic portion and an anionic portion. The word "aliphatic", as used herein, refers to a substantially linear portion, e.g., a hydrocarbon backbone, capable of forming hydrophobic interactions with albumin. The word "anionic", in turn, refers to a charged portion capable of forming further ionic interactions with the albumin

molecule. By the use of a reagent of this invention, these portions can be covalently attached to a surface in a manner that retains their desired function, in order to attract and bind native albumin from blood and other bodily fluids.

In a preferred embodiment, the invention includes photoactivatable molecules having fatty acid functional groups, including polymers having multiple photoactivatable and fatty acid functional groups, as well as heterobifunctional molecules. Photoactivatable polyacrylamide copolymers containing multiple pendant fatty acid analogs and multiple pendant photogroups have been synthesized from acrylamide, a benzophenone-substituted acrylamide, and N-substituted acrylamide monomers containing the fatty acid analog. Photoactivatable polyvinylpyrrolidones have also been prepared in a similar fashion. Polyacrylamide or polyvinylpyrrolidone copolymers with a single end-point photogroup and multiple pendant fatty acid analogs have also been synthesized. Finally, photoactivatable, heterobifunctional molecules having a benzophenone on one end and a fatty acid group on the other end optionally separated by a spacer have been made, wherein that spacer can be a hydrophobic alkyl chain or a more hydrophilic polyethyleneglycol (PEG) chain.

Spacer Group

Suitable spacers ("Y" groups) for use in preparing heterobifunctional reagents of the present invention include any di- or higher-functional spacers capable of covalently attaching a latent reactive group to an aliphatic acid in a manner that permits them both to be used for their intended purpose. Although the spacer may itself provide a desired chemical and/or physical function, preferably the spacer is non-interfering, in that it does not detrimentally affect the use of the aliphatic and ionic portions for their intended purposes. In the case of the polymeric reagents of the invention, the spacer group serves to attach the aliphatic acid to the backbone of the polymer.

The spacer may be either aliphatic or polymeric and contain various heteroatoms such as O, N, and S in place of carbon. Constituent atoms of the spacers need not be aligned linearly. For example, aromatic rings, which lack abstractable hydrogen atoms (as defined below), can be included as part of the spacer design in

those reagents where the latent reactive group functions by initiating covalent bond formation via hydrogen atom abstraction. In its precursor form (i.e., prior to attachment of a photoreactive group and aliphatic acid), a spacer can be terminated with any suitable functionalities, such as hydroxyl, amino, carboxyl, and sulfhydryl groups, which are suitable for use in attaching a photoreactive group and the aliphatic acid by a suitable chemical reaction, e.g., conventional coupling chemistry.

Alternatively, the spacer can be formed in the course of combining a precursor containing (or capable of attaching) the photoreactive group with another containing (or capable of attaching) the aliphatic acid. For example, the aliphatic acid could be reacted with an aliphatic diamine to give an aliphatic amine derivative of the bifunctional aliphatic acid and which could be coupled with a carboxylic acid containing the photogroup. To those skilled in the art, it would be obvious that the photogroup could be attached to any appropriate thermochemical group which would react with any appropriate nucleophile containing O, N or S.

Examples of suitable spacer groups include, but are not limited to, the groups consisting of substituted or unsubstituted alkylene, oxyalkylene, cycloalkylene, arylene, oxyarylene, or aralkylene group, and having amides, ethers, and carbonates as linking functional groups to the photoactivatable group, and the bifunctional aliphatic fatty acid.

The spacer of the invention can also comprise a polymer which serves as a backbone. The polymer backbone can be either synthetic or naturally occurring, and is preferably a synthetic polymer selected from the group consisting of oligomers, homopolymers, and copolymers resulting from addition or condensation polymerization. Naturally occurring polymers, such as polysaccharides, can be used as well. Preferred backbones are biologically inert, in that they do not provide a biological function that is inconsistent with, or detrimental to, their use in the manner described.

Such polymer backbones can include acrylics such as those polymerized from hydroxyethyl acrylate, hydroxyethyl methacrylate, glyceryl acrylate, glyceryl methacrylate, acrylic acid, methacrylic acid, acrylamide and methacrylamide; vinyls

such as polyvinylpyrrolidone and polyvinyl alcohol; nylons such as polycaprolactam; derivatives of polylauryl lactam, polyhexamethylene adipamide and polyhexamethylene dodecanediamide, and polyurethanes; polyethers such as polyethylene oxide, polypropylene oxide, and polybutylene oxide; and biodegradable
5 polymers such as polylactic acid, polyglycolic acid, polydioxanone, polyanhydrides, and polyorthoesters.

The polymeric backbone is chosen to provide a backbone capable of bearing one or more photoreactive groups, and one or more fatty acid functional groups. The polymeric backbone is also selected to provide a spacer between the surface and the
10 various photoreactive groups and fatty acid functional groups. In this manner, the reagent can be bonded to a surface or to an adjacent reagent molecule, to provide the fatty acid functional groups with sufficient freedom of movement to demonstrate optimal activity. The polymer backbones are preferably water soluble, with polyacrylamide and polyvinylpyrrolidone being particularly preferred polymers.

15 Photoreactive Group

In a preferred embodiment one or more photoreactive groups are provided by the X groups attached to the central Y spacer radical. Upon exposure to a suitable light source, each of the photoreactive groups are subject to activation. The term
20 "photoreactive group", as used herein, refers to a chemical group that responds to an applied external energy source in order to undergo active specie generation, resulting in covalent bonding to an adjacent chemical structure (e.g., an aliphatic carbon-hydrogen bond).

Preferred X groups are sufficiently stable to be stored under conditions in which they retain such properties. See, e.g., U.S. Patent No. 5,002,582, the disclosure
25 of which is incorporated herein by reference. Latent reactive groups can be chosen that are responsive to various portions of the electromagnetic spectrum, with those responsive to ultraviolet and visible portions of the spectrum (referred to herein as "photoreactive") being particularly preferred.

Photoreactive aryl ketones are preferred, such as acetophenone, benzophenone,
30 anthraquinone, anthrone, and anthrone-like heterocycles (i.e., heterocyclic analogues

of anthrone such as those having N, O, or S in the 10- position), or their substituted (e.g., ring substituted) derivatives. The functional groups of such ketones are preferred since they are readily capable of undergoing the activation/inactivation/reactivation cycle described herein. Benzophenone is a particularly preferred photoreactive group, since it is capable of photochemical excitation with the initial formation of an excited singlet state that undergoes intersystem crossing to the triplet state. The excited triplet state can insert into carbon-hydrogen bonds by abstraction of a hydrogen atom (for example, from a support surface or target molecule in the solution and in bonding proximity to the agent), thus creating a radical pair. Subsequent collapse of the radical pair leads to formation of a new carbon-carbon bond. If a reactive bond (e.g., carbon-hydrogen) is not available for bonding, the ultraviolet light-induced excitation of the benzophenone group is reversible and the molecule returns to ground state energy level upon removal of the energy source. Hence, photoreactive aryl ketones are particularly preferred.

The azides constitute a preferred class of latent reactive groups and include arylazides ($C_6R_5N_3$) such as phenyl azide and particularly 4-fluoro-3-nitrophenyl azide, acyl azides ($-CO-N_3$) such as ethyl azidoformate, phenyl azidoformate, sulfonyl azides (SO_2-N_3) such as benzenesulfonyl azide, and phosphoryl azides $(RO)_2PON_3$ such as diphenyl phosphoryl azide and diethyl phosphoryl azide. Diazo compounds constitute another class of photoreactive groups and include diazoalkanes ($-CHN_2$) such as diazomethane and diphenyldiazomethane, diazoketones ($-CO-CHN_2$) such as diazoacetophenone and 1-trifluoromethyl-1-diazo-2-pentanone, diazoacetates ($-CO-CN_2-CO-O-$) such as t-butyl alpha diazoacetoacetate. Other photoreactive groups include aliphatic azo compounds such as azobisisobutyronitrile, diazirines ($-CHN_2$) such as 3-trifluoromethyl-3-phenyldiazirine and ketenes ($-CH=C=O$) such as ketene and diphenylketene.

Upon activation of the photoreactive groups, the coating adhesion molecules are covalently bound to each other and/or to the material surface by covalent bonds through

residues of the photoreactive groups. Exemplary photoreactive groups, and their residues upon activation, are shown as follows.

	<u>Photoreactive Group</u>	<u>Residue Functionality</u>
	aryl azides	amine $R-NH-R'$
5	acyl azides	amide $R-CO-NH-R'$
	azidoformates	carbamate $R-O-CO-NH-R'$
	sulfonyl azides	sulfonamide $R-SO_2-NH-R'$
	phosphoryl azides	phosphoramidate $(RO)_2PO-NH-R'$
	diazoalkanes	new C-C bond
10	diazoketones	new C-C bond and ketone
	diazoacetates	new C-C bond and ester
	beta-keto-alpha-diazoacetates	new C-C bond and beta-ketoester
	aliphatic azo	new C-C bond
	diazirines	new C-C bond
15	ketenes	new C-C bond
	photoactivated ketones	new C-C bond and alcohol

Preparation of Reagents

Reagents of the present invention can be prepared by any suitable means, depending upon the selection of either a heterobifunctional reagent or a polymeric reagent. In the case of the heterobifunctional reagents, the fatty acid residue is provided by a fatty acid possessing a chemically reactive group on the alkyl chain which permits covalent coupling of the remainder of the heterobifunctional molecule to the fatty acid with preservation of the carboxylic acid functionality. Preferably, the site of the reactive group is in close proximity to the carboxylic acid group so as to minimize effects on the binding activity of the hydrophobic alkyl chain. Most preferably, the fatty acid residue can be provided by a compound such as n-tetradecylsuccinic anhydride (TDSA). Reaction of such a molecule with a second molecule possessing a nucleophilic species such as a primary amine results in opening of the anhydride ring to give a fatty acid with an amide linkage to the remainder of the molecule. This reaction generates a pair of regioisomers depending upon the direction

of the anhydride ring opening. The second molecule in this reaction can be provided by a spacer group, with or without a photoactivatable group, which possesses a group capable of reaction with the fatty acid compound. Most preferably, this spacer group possesses an amine which is highly reactive with an anhydride species. The spacer
5 group is typically a bifunctional molecule which can have the photoactivatable group attached prior to reaction with the fatty acid derivative or the reverse order of reaction can be used. The bifunctional spacer can be either heterobifunctional or homobifunctional, with the former requiring a differential reactivity in the first and second reaction steps and the latter requiring an efficient method of separating the
10 monofunctionalized spacer following the first reaction. Optionally, no spacer is required and a photoactivatable group possessing functionality capable of reaction with the fatty acid derivative can be used. The above examples are nonlimiting and the methods of accomplishing these coupling reactions are apparent to those skilled in the art.

15 Polymeric reagents of the invention can be prepared by derivatization of preformed polymers possessing reactive groups along the backbone of the polymer capable of reaction with the photoactivatable groups and the fatty acid derivatives. For example, polyacrylamide, polyvinylpyrrolidone, or siloxanes functionalized with amine groups along the backbone, with or without a spacer group, can be reacted with
20 4-benzoylbenzoyl chloride (BBA-Cl) and TDSA to provide the photoactivatable and fatty acid ligands respectively. Alternatively, the photoactivatable and fatty acid groups can be prepared in the form of polymerizable monomers which can then be copolymerized with themselves and other monomers to provide polymers of the invention. In a further embodiment of the invention, the photoactivatable group can
25 be introduced in the form of a chain transfer agent along with the fatty acid monomer and other comonomers so as to provide a polymer having the photoactivatable group at the end of the polymer chain. For example, a chain transfer agent possessing two derivatized benzophenones as the photoactivatable groups and a mercaptan as the chain transfer agent can be used to copolymerize a fatty acid monomer and acrylamide
30 or N-vinylpyrrolidone monomers to provide polymers of the invention. Alternatively,

this polymer could be prepared with reactive groups along the backbone, followed by reaction with a fatty acid derivative.

Surfaces and Methods of Attachment

The reagent of the present invention can be used to modify any suitable surface.

- 5 Where the latent reactive group is a photoreactive group of the preferred type, it is particularly preferred that the surface provide abstractable hydrogen atoms suitable for covalent bonding with the activated group.

- Plastics such as polyolefins, polystyrenes, poly(methyl)methacrylates, polyacrylonitriles, poly(vinylacetates), poly (vinyl alcohols), chlorine-containing
10 polymers such as poly(vinyl) chloride, polyoxymethylenes, polycarbonates, polyamides, polyimides, polyurethanes, phenolics, amino-epoxy resins, polyesters, silicones, cellulose-based plastics, and rubber-like plastics can all be used as supports, providing surfaces that can be modified as described herein. See generally, "Plastics", pp. 462-464, in Concise Encyclopedia of Polymer Science and Engineering,
15 Kroschwitz, ed., John Wiley and Sons, 1990, the disclosure of which is incorporated herein by reference. In addition, supports such as those formed of pyrolytic carbon and silylated surfaces of glass, ceramic, or metal are suitable for surface modification.

- Any suitable technique can be used for reagent binding to a surface, and such techniques can be selected and optimized for each material, process, or device. The
20 reagent can be successfully applied to clean material surfaces as listed above by spray, dip, or brush coating of a solution of the fatty acid binding reagent. The surface may be air-dried prior to illumination or the surface can be illuminated while submerged in the coating solution. The photoreactive group is energized via an external stimulation (e.g., exposure to a suitable light source) to form, via free active specie generation, a
25 covalent bond between the reagent and either another polybifunctional reagent molecule or the biomaterial surface. This coating method is herein termed the "one step coating method", since photoreactive coupling chemistry attaches an invention polymer to a biomaterial surface, and no subsequent steps are required to add the bioactive group. The external stimulation that is employed desirably is






electromagnetic radiation, and preferably is radiation in the ultraviolet, visible or infrared regions of the electromagnetic spectrum.





The "two-step" method would involve a first step of photocoupling a hydrocarbon backbone to the surface, followed by a second step of attaching (e.g., thermochemically) one or more fatty acid derivatives to the immobilized backbone. For example, this two step approach could involve covalently attaching a photoreactive hydrocarbon backbone containing nucleophiles which could be used to thermochemically couple fatty acid derivatives to the surface, or directly attaching thermochemical groups (e.g. amines) to the surface, followed by thermochemical attachment of one or more fatty acid derivatives.

Alternatively, chemically reactive groups can be introduced on the surface by a variety of non-photochemical methods, followed by chemical coupling of the fatty acid group to the modified surface. For example, amine groups can be introduced on a surface by plasma treatment with a mixture of methane and ammonia and the resulting amines can then be reacted with TDSA to chemically couple the fatty acid derivative to the surface through an amide linkage. When desired, other approaches can be used for surface modification using the reagent of the present invention. This approach is particularly useful in those situations in which a support is difficult to modify using conventional chemistry, or for situations that require exceptional durability and stability of the target molecule on the surface.

Examples






The invention will be further described with reference to the following non-limiting Examples, which incorporate the following table of formulas. It will be apparent to those skilled in the art that many changes can be made in the embodiments described without departing from the scope of the present invention. Thus the scope of the present invention should not be limited to the embodiments described in this application, but only by embodiments described by the language of the claims and the equivalents of those embodiments. Unless otherwise indicated, all percentages are by weight.





Formula	Compound/ Example	Notation
	1/1	4-Benzoyl- benzoyl chloride
	2/2	4-Bromo- methyl- benzo- phenone
	3/3	Poly- (ethylene glycol) ₂₀₀ Mono-4- benzoyl- benzyl Ether
	4/4	Poly(ethylene glycol) ₂₀₀ Mono-4- benzoyl- benzyl Ether Mono- methane- sulfonate
	5/5	Mono- aminopoly (ethylene glycol) ₂₀₀ Mono-4- benzoyl- benzyl Ether


Formula	Compound/ Example	Notation
	6/6	Mono-2-(carboxymethyl) hexadecanamidopoly (ethylene glycol) ₂₀₀ Mono-4-benzoylbenzyl Ether
	7/6	Mono-3-carboxyheptadecanamidopoly (ethylene glycol) ₂₀₀ Mono-4-benzoylbenzyl Ether
	8/7	Mono-2-(carboxymethyl) hexadecanamidotetra (ethylene glycol) Mono-4-benzoylbenzyl Ether
	9/7	Mono-3-carboxyheptadecanamidotetra (ethylene glycol) Mono-4-benzoylbenzyl Ether

Formula	Compound/ Example	Notation
	10/8	N-[2-(4-Benzoyl-benzyloxy)ethyl]-2-(carboxy-methyl)hexadecanamide
	11/8	N-[2-(4-Benzoyl-benzyloxy)ethyl]-3-carboxy-hepta-decanamide
	12/9	N-[12-(Benzoyl-benzyloxy)dodecyl]-2-(carboxy-methyl)hexadecanamide
	13/9	N-[12-(Benzoyl-benzyloxy)dodecyl]-3-carboxy-heptadeca-namide
	14/10	N-[3-(4-Benzoyl-benzamido)propyl]-2-(carboxy-methyl)hexadecanamide

Formula	Compound/ Example	Notation
	15/10	N-[3-(4-Benzoyl-benzamido)propyl]-3-carboxy-hepta-decanamide
	16/11	N-(3-Benzoyl-phenyl)-2-(carboxy-methyl)hexadeca-namide
	17/11	N-(3-Benzoyl-phenyl)-3carboxy-hepta-decanamide
	18/12	N-(4-Benzoyl-phenyl)-2-(carboxy-methyl)hexadeca-namide
	19/12	N-(4-Benzoyl-phenyl)-3-carboxy-hepta-decanamide
	20/13	Mono-hexa-decanamido-poly(ethylene glycol) ₂₀₀ Mono-4-benzoyl-benzyl Ether

Formula	Compound/ Example	Notation
 $\text{C}_6\text{H}_5\text{C}(=\text{O})\text{C}_6\text{H}_4\text{CH}_2(\text{OCH}_2\text{CH}_2)_x\text{NH}-\text{C}(=\text{O})-\text{CH}_2\text{CH}_2\text{CO}_2\text{H}$	21/14	Mono-3- Carboxy- propana- midopoly (ethylene glycol) ₂₀₀ Mono-4- benzoyl- benzyl Ether
 $\text{C}_6\text{H}_5\text{C}(=\text{O})\text{C}_6\text{H}_4\text{CH}_2\text{O}(\text{CH}_2)_{15}\text{CH}_3$	22/15	Hexadecyl 4- benzoyl- benzil ether
 $\text{C}_6\text{H}_5\text{C}(=\text{O})\text{C}_6\text{H}_4\text{CH}_2(\text{OCH}_2\text{CH}_2)_x\text{O}(\text{CH}_2)_{15}\text{CH}_3$	23/16	Poly(ethylene glycol) ₂₀₀ Monohexa- decyl Mono-4- benzoyl- benzyl Ether
 $\text{C}_6\text{H}_5\text{C}(=\text{O})\text{C}_6\text{H}_4\text{CH}_2(\text{OCH}_2\text{CH}_2)_x\text{O}(\text{CH}_2)_{15}\text{CO}_2\text{H}$	24/17	Poly(ethylene glycol) ₂₀₀ Mono-15- carboxy- pentadecyl Mono-4- benzoyl- benzyl Ether
 $\text{C}_6\text{H}_5\text{C}(=\text{O})\text{C}_6\text{H}_4\text{CH}_2(\text{OCH}_2\text{CH}_2)_x\text{NH}-\text{C}(=\text{O})-(\text{CH}_2)_{14}\text{CO}_2\text{H}$	25/18	Mono-15- carboxy- penta- decana- midopoly (ethylene glycol) ₂₀₀ Mono-4- benzoyl- benzyl

Formula	Compound/ Example	Notation
		Ether
	26/19	N-[3-Methacrylamido) propyl]-2-(carboxymethyl)-hexadecanamide
	27/19	N-[3-Methacrylamido) propyl]-3-carboxyheptadecanamide
	28/20	N-[3-(4-Benzoylbenzamido) propyl]-methacrylamide
	29/21	N-(2-Mercaptoethyl)-3,5-bis(4-benzoylbenzyloxy)benzamide




Compound/ Example

30/22

Notation


Photo-reactive Endpoint Copolymer of Acrylamide and Fatty Acid Monomers

FormulaCompound/ Example

31/23

Notation

Photo-reactive Random Copolymer of Acrylamide
and Fatty Acid Monomers

FormulaNotationCompound/ ExamplePhoto-reactive Endpoint Copolymer of N-Vinyl-pyrrolidone
and Fatty Acid Monomers

32A-C/24

SUBSTITUTE SHEET (RULE 26)

Formula	Compound/ Example	Notation
$\left[\begin{array}{c} \text{H} \\ \\ \text{CH}_2 - \text{C} - \text{N} \\ \quad \quad \quad \diagup \\ \text{O} \quad \quad \quad \text{Cyclopentyl} \end{array} \right]$		
$\left[\begin{array}{c} \text{CH}_3 \\ \\ \text{CH}_2 - \text{C} - \text{C}(=\text{O}) - \text{N} - (\text{CH}_2)_3 - \text{N} - \text{C}(=\text{O}) - \text{CH}_2 - \text{CH}(\text{CO}_2\text{H}) - (\text{CH}_2)_{13} - \text{CH}_3 \end{array} \right]$		
$\left[\begin{array}{c} \text{CH}_3 \\ \\ \text{CH}_2 - \text{C} - \text{C}(=\text{O}) - \text{N} - (\text{CH}_2)_3 - \text{N} - \text{C}(=\text{O}) - \text{CH}_2 - \text{CH}(\text{CO}_2\text{H}) - (\text{CH}_2)_{13} - \text{CH}_3 \end{array} \right]$		
$\left[\begin{array}{c} \text{CH}_3 \\ \\ \text{CH}_2 - \text{C} - \text{C}(=\text{O}) - \text{N} - (\text{CH}_2)_3 - \text{N} - \text{C}(=\text{O}) - \text{C}_6\text{H}_4 - \text{C}(=\text{O}) - \text{C}_6\text{H}_5 \end{array} \right]$		

33A-D/25

Photoreactive Random Copolymer of N-Vinylpyrrolidone and Fatty Acid Monomers

Formula	Compound/ Example	Notation
$\left[\text{CH}_3 - \text{Si} - \text{O} - \text{CH}_3 \right]$	$\left[\text{CH}_3 - \text{Si} - \text{O} - \text{CH}_3 - \text{NH} - \text{C}=\text{O} - \text{CH}_2 - \text{CH} - (\text{CH}_2)_{13} - \text{CH}_3 \right]$	Photo-reactive Siloxane Copolymer Containing Fatty Acid Ligands
$\left[\text{CH}_3 - \text{Si} - \text{O} - \text{CH}_3 - \text{NH} - \text{C}=\text{O} - \text{CH}_2 - \text{CH} - (\text{CH}_2)_{13} - \text{CH}_3 \right]$	$\left[\text{CH}_3 - \text{Si} - \text{O} - \text{CH}_3 - \text{NH} - \text{C}=\text{O} - \text{CH}_2 - \text{CH} - (\text{CH}_2)_{13} - \text{CH}_3 \right]$	
$\left[\text{CH}_3 - \text{Si} - \text{O} - \text{CH}_3 - \text{NH} - \text{C}=\text{O} - \text{C}_6\text{H}_4 - \text{C}(=\text{O}) - \text{C}_6\text{H}_5 \right]$	$\left[\text{CH}_3 - \text{Si} - \text{O} - \text{CH}_3 - \text{NH} - \text{C}=\text{O} - \text{CH}_2 - \text{CH} - (\text{CH}_2)_{13} - \text{CH}_3 \right]$	

Example 1

Preparation of 4-Benzoylbenzoyl Chloride (BBA-Cl) (Compound 1)

4-Benzoylbenzoic acid (BBA), 1.0 kg (4.42 moles), was added to a dry 5 liter Morton flask equipped with reflux condenser and overhead stirrer, followed by the addition of 645 ml (8.84 moles) of thionyl chloride and 725 ml of toluene. Dimethylformamide (DMF), 3.5 ml, was then added and the mixture was heated at reflux for 4 hours. After cooling, the solvents were removed under reduced pressure and the residual thionyl chloride was removed by three evaporations using 3 x 500 ml of toluene. The product was recrystallized from toluene/hexane (1/4) to give 988 g (91% yield) after drying in a vacuum oven. Product melting point was 92-94°C. Nuclear magnetic resonance (NMR) analysis at 80 MHz was consistent with the desired product. The final compound was stored for use in the preparation of photoactivatable compounds, as described for instance in Examples 10 and 20.

Example 2

Preparation of 4-Bromomethylbenzophenone (BMBP) (Compound 2)

4-Methylbenzophenone, 750 g (3.82 moles), was added to a 5 liter Morton flask equipped with an overhead stirrer and dissolved in 2850 ml of benzene. The solution was then heated to reflux, followed by the dropwise addition of 610 g (3.82 moles) of bromine in 330 ml of benzene. The addition rate was approximately 1.5 ml/min and the flask was illuminated with a 90 watt (90 joule/sec) halogen spotlight to initiate the reaction. A timer was used with the lamp to provide a 10% duty cycle (on 5 seconds, off 40 seconds), followed in one hour by a 20% duty cycle (on 10 seconds, off 40 seconds). At the end of the addition, the product was analyzed by gas chromatography and was found to contain 71% of the desired 4-bromomethylbenzophenone, 8 % of the dibromo product, and 20% unreacted 4-methylbenzophenone. After cooling, the reaction mixture was washed with 10 g of sodium bisulfite in 100 ml of water, followed by washing with 3 x 200 ml of water. The product was dried over sodium sulfate and recrystallized twice from toluene/hexane (1/3 by volume (v/v)). After drying under vacuum, 635 g of BMBP were isolated, providing a yield of 60% and having a melting point of 112-114°C.

Analysis on an NMR spectrometer was consistent with the desired product. The final compound was stored for use in the preparation of photoactivatable compounds, as described for instance in Examples 3, 7, 8, 9, 15, and 21.

Example 3

5 Preparation of Poly(ethylene glycol)₂₀₀ Mono-4-benzoylbenzyl Ether (Compound 3)

The poly(ethylene glycol)₂₀₀ (PEG), 72.72 g (0.363 mol), was azeotroped with 200 ml of toluene for two hours to remove moisture, followed by the removal of excess toluene under vacuum. The PEG residue was then dissolved in 400 ml of anhydrous tetrahydrofuran (THF) while stirring under argon at 4°C. Sodium hydride,
10 2.90 g of a 60% mixture in mineral oil (72.5 mmol), was added in portions and the mixture was stirred 1 hour at room temperature. BMBP, 20.0 g (72.7 mmol), prepared according to the general method described in Example 2, was added as a solution in 100 ml of THF over a 2 hour period and the mixture was stirred 16 hours at room temperature under argon. The reaction was quenched with aqueous
15 ammonium chloride (36 g in 200 ml of water) and the organic solvent was removed under vacuum. The residue was dissolved in brine, extracted with chloroform, and the resulting organic extracts were dried over sodium sulfate. The product was isolated as a viscous oil by adding the chloroform solution to diethyl ether, resulting in precipitation of 27.64 g of the desired product. The product was used without
20 additional purification. Analysis on an NMR spectrometer was consistent with the desired product.

Example 4

Preparation of Poly(ethylene glycol)₂₀₀ Mono-4-benzoylbenzyl Ether Monomethanesulfonate (Compound 4)

25 Compound 3, 3.0 g (7.61 mmol), prepared according to the general method described in Example 3, was dissolved in 25 ml of methylene chloride, followed by the addition of 1.5 g (14.8 mmol) of triethylamine (TEA). The mixture was cooled on an ice bath under argon and 1.3 g (11.3 mmol) of methanesulfonyl chloride (MsCl) were added dropwise over a 10 minute period. The reaction temperature was
30 allowed to rise to ambient temperature overnight. The precipitated salts were

removed by filtration and the solvent was removed under vacuum. The residue was dissolved in toluene and filtered to remove solids, followed by evaporation under vacuum to give 3.01 g of product. No further purification of the product was done at this point. Analysis on an NMR spectrometer was consistent with the desired product.

Example 5

Preparation of Monoaminopoly(ethylene glycol)₂₀₀ Mono-4-benzoylbenzyl Ether
(Compound 5)

Compound 4, 17.97 g (38.07 mmol), prepared according to the general method described in Example 4, was dissolved in 100 ml of anhydrous THF in a thick-walled tube, followed by the addition of 100 ml of concentrated ammonium hydroxide. The tube was sealed and the two phase mixture was stirred vigorously at 65°C for 16 hours. The solvent was removed under vacuum and the resulting residue was dissolved in chloroform. The product was loaded on a silica gel flash chromatography column and eluted with chloroform/acetone/acetic acid (60/40/1 v/v) until all of the less polar impurities were removed. The product was then eluted with chloroform/methanol/acetic acid/water (85/15/1/1 v/v). The fractions which were UV, ninhydrin, and Dragendorff positive were pooled and the solvent was removed under vacuum to give 8.63 g of product. Analysis on an NMR spectrometer was consistent with the desired product.

20 Example 6

Preparation of Mono-2-(carboxymethyl)hexadecanamidopoly(ethylene glycol)₂₀₀
Mono-4-benzoylbenzyl Ether (Compound 6) and Mono-3-
carboxyheptadecanamidopoly(ethylene glycol)₂₀₀ Mono-4-benzoylbenzyl Ether
(Compound 7)

25 Compound 5, 3.03 g (7.71 mmol), prepared according to the general method described in Example 5, and TEA, 2.24 g (22.1 mmol), were dissolved in 30 ml of methylene chloride, followed by the addition of 2.40 g (8.10 mmol) of TDSA as the solid. The reaction mixture was stirred 18 hours at room temperature under argon. The solvents were removed under vacuum and the resulting oil was purified by silica
30 gel flash chromatography using a solvent gradient: 500 ml of ether/hexane (75/25

v/v); 500 ml of ether/hexane/acetic acid (75/25/1 v/v); chloroform/acetone/acetic acid (60/40/1 v/v); and chloroform/methanol/acetic acid/water (85/15/1/1 v/v). The fractions were pooled to give two separate UV and Dragendorff positive materials representing the regioisomers resulting from ring opening of the anhydride ring.

5 Evaporation of solvent gave 1.35 g of product in one fraction and 0.893 g in the second. Analysis on an NMR spectrometer was consistent with the desired products.

Example 7

Preparation of Mono-2-(carboxymethyl)hexadecanamidotetra(ethylene glycol) Mono-4-benzoylbenzyl Ether (Compound 8) and Mono-3-

carboxyheptadecanamidotetra(ethylene glycol) Mono-4-benzoylbenzyl Ether (Compound 9)

The tetraethylene glycol (TEG), 7.063 g (36.4 mmol), was azeotroped with 200 ml of toluene for two hours to remove moisture, followed by the removal of excess toluene under vacuum. The TEG residue was then dissolved in 70 ml of

15 anhydrous THF while stirring under argon on an ice bath. Sodium hydride, 1.45 g of a 60% mixture in mineral oil (36.3 mmol), was added and the mixture was stirred 1 hour at room temperature. BMBP, 5.0 g (18.2 mmol), prepared according to the general method described in Example 2, was added and the mixture was stirred 16 hours at room temperature under argon. The reaction was quenched with aqueous

20 ammonium chloride (9 g in 40 ml of water) and the organic solvent was removed under vacuum. The residue was dissolved in saturated brine, extracted with chloroform, and the resulting organic extracts were dried over sodium sulfate. The product was isolated as a viscous oil by adding the chloroform solution to diethyl ether. The crude product, 7.6 g, was used without additional purification.

25 The entire product from above was dissolved in 200 ml of methylene chloride, followed by the addition of 3.96 g (39.1 mmol) of TEA. The mixture was cooled to 4°C under argon and 3.35 g (29.2 mmol) of MsCl were added. After 6 hours, an additional 1 ml each of TEA and MsCl were added and the reaction was left to stir for 16 hours to insure complete reaction. The precipitated salts were removed by

30 filtration and the solvent was removed under vacuum. The residue was dissolved in

toluene and filtered to remove solids, followed by evaporation under vacuum. No further purification of the product was done at this point.

The entire mesylate product from above was dissolved in 50 ml of THF in a thick-walled glass tube, followed by the addition of 50 ml of concentrated ammonium hydroxide. The tube was sealed and the two phase mixture was stirred vigorously at 65°C for 16 hours. The solvent was removed under vacuum and the resulting residue was dissolved in 20 ml of chloroform. After drying over sodium sulfate, the product was precipitated by addition of the chloroform solution to diethyl ether resulting in approximately 4.5 g of a brown viscous oil. A portion of the product, approximately 1 g, was purified by silica gel flash chromatography using a solvent gradient of ether/hexane/acetic acid (75/25/1 v/v), followed by chloroform/acetone/acetic acid (60/40/1 v/v), and chloroform/ethanol/water/acetic acid (85/15/1/1 v/v). A total of 220 mg of purified product were isolated. Analysis on an NMR spectrometer was consistent with the desired product.

The amine product from above, 0.220 g (0.568 mmol), and TEA, 63 mg (0.623 mmol), were dissolved in 20 ml of methylene chloride, followed by the addition of 0.185 g (0.625 mmol) of TDSA. The reaction mixture was stirred 48 hours at room temperature under argon. The solvents were removed under vacuum and the resulting oil was purified by silica gel flash chromatography using a chloroform/methanol/water/acetic acid (85/15/1/1 v/v). The appropriate fractions were pooled, evaporated, redissolved in chloroform, and dried over sodium sulfate. Evaporation of solvent gave 234 mg of a waxy solid as a mixture of regioisomers resulting from opening of the anhydride ring. Analysis on an NMR spectrometer was consistent with the desired products.

25

Example 8

Preparation of N-[2-(4-Benzoylbenzyloxy)ethyl]-2-(carboxymethyl)hexadecanamide (Compound 10) and N-[2-(4-Benzoylbenzyloxy)ethyl]-3-carboxyheptadecanamide (Compound 11)

Anhydrous ethanolamine, 1.00 g (16.4 mmol), was dissolved in 5 ml of anhydrous THF with stirring under argon. Sodium hydride, 0.655 g (16.4 mmol) of a

60% mineral oil dispersion, was added as a solid followed by an additional 5 ml of anhydrous THF. The resulting mixture was stirred at room for 45 minutes at which time no more hydrogen evolution was observed. The BMBP, 4.50 g (16.4 mmol), prepared according to the general method described in Example 2, was added as a solution in 25 ml of THF over a 30 minute period. The reaction was allowed to stir overnight at room temperature. The reaction was quenched with water and the product was extracted with chloroform. The organic extract was washed with 0.1 N HCl and the aqueous solution was washed one time with chloroform. The aqueous was then evaporated under vacuum, dissolved in 10% methanol in chloroform (v/v) and dried over sodium sulfate. Evaporation of solvent gave 2.62 g of a pale yellow solid which was used without additional purification.

The above amine, 0.625 g (2.14 mmol), and TDSA, 0.467 g (1.57 mmol), were dissolved in 10 ml of methylene chloride, followed by the addition of 660 μ l (4.74 mmol) of TEA. The resulting solution was stirred at room temperature for 16 hours to complete the reaction. The product was diluted with water and treated with 5% HCl, followed by separation of the organic layer and drying over sodium sulfate. The solvent was removed under vacuum and the product was purified using silica gel flash chromatography with a solvent gradient of chloroform followed by 2.5% and 5 % (v/v) methanol in chloroform. The appropriate fractions were pooled to give 357 mg of product as a pair of regioisomers resulting from the opening of the anhydride ring. Analysis on an NMR spectrometer was consistent with the desired products.

Example 9

Preparation of N-[12-(Benzoylbenzyloxy)dodecyl]-2-(carboxymethyl)hexadecanamide (Compound 12) and N-[12-(Benzoylbenzyloxy)dodecyl]-3-carboxyheptadecanamide (Compound 13)

1,12-Dodecanediol, 5.0 g (24.7 mmol), was dissolved in 50 ml of anhydrous THF in a dry flask under nitrogen. The sodium hydride, 0.494 g of a 60% dispersion in mineral oil (12.4 mmol), was added in portions over a five minute period. The resulting mixture was stirred at room temperature for one hour. BMBP, 3.40 g (12.4 mmol), prepared according to the general method described in Example 2, was added

- as a solid along with sodium iodide (0.185 g, 1.23 mmol) and tetra-n-butylammonium bromide (0.398 g, 1.23 mmol). The mixture was stirred at a gentle reflux for 24 hours. The reaction was then cooled, quenched with water, acidified with 5% HCl, and extracted with chloroform. The organic extracts were dried over sodium sulfate and the solvent was removed under vacuum. The product was purified on a silica gel flash chromatography column using chloroform to elute non-polar impurities, followed by elution of the product with chloroform/ethyl acetate (80/20 v/v). Pooling of appropriate fractions and evaporation of solvent gave 3.42 g of product, a 70% yield. Analysis on an NMR spectrometer was consistent with the desired product.
- 10 The above alcohol, 1.30 g (3.28 mmol), was dissolved in 13 ml of anhydrous methylene chloride, followed by 0.829 g (8.19 mmol) of TEA and cooling on an ice bath under argon. MsCl, 0.563 g (4.91 mmol), was added dropwise over a five minute period, followed by stirring at room temperature for 16 hours. The reaction was diluted with water, acidified with 5% HCl, and extracted with chloroform. The organic extracts were dried over sodium sulfate and evaporated to give 1.56 g of a yellow oil. This product was used without further purification. Analysis on an NMR spectrometer was consistent with the desired product.
- 15 The above mesylate, 1.56 g (3.28 mmol), was dissolved in 25 ml of THF in a thick-walled tube, followed by the addition of 25 ml of ammonium hydroxide. The tube was sealed and the mixture was stirred vigorously for 72 hours at 80°C. The mixture was treated with 200 ml of water and the product was extracted with chloroform. The organic extracts were dried over sodium sulfate and the product was purified on a silica gel flash chromatography column. The column was eluted with chloroform and chloroform/methanol (95/5 v/v) until the less polar impurities were removed, followed by elution of the desired product using chloroform/methanol/ammonium hydroxide (70/25/5 v/v). Pooling of the ninhydrin and UV active fractions and evaporation of solvent gave 0.526 g of product, a 40% yield. Analysis on an NMR spectrometer was consistent with the desired product.
- 25 The above amine, 0.440 g (1.11 mmol), was dissolved in 7 ml of methylene chloride, followed by 0.329 g (1.11 mmol) of TDSA and 0.337 g (3.33 mmol) of
- 30

TEA. The resulting mixture was stirred at room temperature for 36 hours. The reaction was then diluted with water, acidified with 5% HCl, and extracted with chloroform. The organic extracts were dried over sodium sulfate and the residue after evaporation was purified on silica gel flash chromatography. A solvent gradient of
5 chloroform, 2.5% methanol in chloroform (v/v), and 5% methanol in chloroform (v/v) was used to elute the product. A total of 378 mg of product were isolated as a partially resolved pair of regioisomers resulting from opening of the anhydride ring. Analysis on an NMR spectrometer was consistent with the desired products.

Example 10

10 Preparation of N-[3-(4-Benzoylbenzamido)propyl]-2-
 (carboxymethyl)hexadecanamide (Compound 14) and N-[3-(4-
 Benzoylbenzamido)propyl]-3-carboxyheptadecanamide (Compound 15)

1,3-Diaminopropane, 1.910 kg (25.77 mol), was placed in a 12 liter Morton flask and diluted with 1000 ml of methylene chloride. After cooling to below 10°C on
15 an ice bath, a solution of 1.005 kg (5.175 mol) of t-butyl phenyl carbonate in 250 ml of methylene chloride was added slowly to the diamine while keeping the temperature below 15°C at all times. Once the addition was complete, the mixture was warmed to room temperature for 2 hours to complete the reaction. The reaction was further
diluted with 900 ml of methylene chloride, followed by the addition of 500 g of ice
20 and a slow addition of 2500 ml of 2.2 N NaOH. The organic layer was separated and the basic aqueous solution was extracted with 3 x 1250 ml of methylene chloride, keeping each extract separate. Each of these separate extracts was successively
washed with 1250 ml of 0.6 N NaOH, beginning with the first extract and proceeding to the last. This wash procedure was repeated and the organic extracts were combined
25 and dried over sodium sulfate. Evaporation of solvent yielded 825 g of product for a 92% yield. This product was used without any further purification. Analysis on an NMR spectrometer was consistent with the desired product.

The above amine, 0.774 g (4.44 mmol), was diluted with 20 ml of anhydrous methylene chloride, followed by the addition of 1.24 g (12.3 mmol) of TEA and a
30 dropwise addition of 10 ml of anhydrous methylene chloride containing of 1.0 g (4.09

mmol) of BBA-Cl, prepared according to the general method described in Example 1, After stirring 1.5 hours at room temperature, the reaction was diluted with water and acidified with 1 N HCl. The product was extracted with chloroform and the organic extracts were dried over sodium sulfate. Silica gel flash chromatography using
5 chloroform/methanol (90/10 v/v) gave 1.68 g of product, slightly greater than theoretical because of solvent residues. Mass spectral analysis confirmed the desired product.

The above product, 1.5 g (3.95 mmol), was dissolved in 10 ml of trifluoroacetic acid under a nitrogen atmosphere. After stirring 3 hours at room
10 temperature to remove the t-butyloxycarbonyl (t-BOC) protecting group, the solvent was removed under reduced pressure and the product was purified using silica gel flash chromatography. After removal of the less polar impurities with chloroform/methanol (90/10 v/v), the eluting solvent was switched to chloroform/methanol/ammmonium hydroxide (70/25/5 v/v) for isolation of the desired
15 product. Pooling of the appropriate fractions and evaporation of solvent gave 1.77 g of product. Analysis on an NMR spectrometer was consistent with the desired product.

A portion of above amine product, 0.500 g (1.77 mmol), was dissolved in 10 ml of anhydrous methylene chloride under an argon atmosphere. TEA, 0.197 g (1.95
20 mmol), was added, followed by 0.577 g (1.95 mmol) of TDSA. The reaction was stirred for four hours at room temperature. The mixture was diluted with water, extracted with methylene chloride, and the organic extracts were dried over sodium sulfate. After vacuum removal of solvents, the product was purified by silica gel flash chromatography using a chloroform/methanol/acetic acid/water (85/15/1/1 v/v)
25 system. A repeat chromatography using a 0→5% methanol in chloroform (v/v) system gave a more pure product. A total of 0.259 g of product (25% yield) were isolated as a pair of regioisomers resulting from opening of the anhydride ring. Analysis on an NMR spectrometer was consistent with the desired products.

Example 11

Preparation of N-(3-Benzoylphenyl)-2-(carboxymethyl)hexadecanamide (Compound 16) and N-(3-Benzoylphenyl)-3-carboxyheptadecanamide (Compound 17)

The 3-aminobenzophenone, 0.500 g (2.53 mmol), was dissolved in 5.0 ml of dry DMF along with 0.512 g (5.06 mmol) of TEA and 0.030 g (0.25 mmol) of 4-dimethylaminopyridine. While stirring under argon, 0.826 g (2.79 mmol) of TDSA were added and the resulting solution was stirred at 45°C overnight. The reaction was diluted with water and the desired product was extracted with chloroform. After drying over sodium sulfate, the solvent was removed and the product was purified on silica gel flash chromatography. The less polar impurities were eluted with chloroform and the product was eluted with a 2.5→5.0% methanol in chloroform (v/v) gradient. A total of 1.048 g of product were isolated with a partial resolution of the two regioisomers resulting from opening of the anhydride ring system. Analysis on an NMR spectrometer was consistent with the desired products.

15

Example 12

Preparation of N-(4-Benzoylphenyl)-2-(carboxymethyl)hexadecanamide (Compound 18) and N-(4-Benzoylphenyl)-3-carboxyheptadecanamide (Compound 19)

The 4-aminobenzophenone, 0.500 g (2.53 mmol), was dissolved in 7.0 ml of dry DMF along with 0.512 g (5.06 mmol) of TEA and 0.030 g (0.25 mmol) of 4-dimethylaminopyridine. While stirring under argon, 0.826 g (2.79 mmol) of TDSA were added and the resulting solution was stirred at 55°C for 80 hours. At this time, thin layer chromatography (TLC) revealed partial conversion to a less polar UV active product. The reaction was diluted with water and the desired product was extracted with chloroform. After drying over sodium sulfate, the solvent was removed and the product was purified on silica gel flash chromatography. The less polar impurities were eluted with chloroform and the product was eluted with a 2.5→5.0% methanol in chloroform (v/v) gradient. A total of 0.753 g of product were isolated with a partial resolution of the two regioisomers resulting from opening of the anhydride ring system. Analysis on an NMR spectrometer was consistent with the desired products.

25

Example 13

Preparation of Monohexadecanamidopoly(ethylene glycol)₂₀₀ Mono-4-benzoylbenzyl Ether (Compound 20)

Compound 5, 0.914 g (2.32 mmol), prepared according to the general method described in Example 5, was dissolved in 10 ml of anhydrous chloroform with stirring under argon. TEA, 0.516 g (5.10 mmol), was added followed by the slow dropwise addition of 0.701 g (2.55 mmol) of palmitoyl chloride. The resulting mixture was stirred at room temperature overnight. The reaction was diluted with water and the product was extracted with chloroform. After drying over sodium sulfate, the solvent was removed under vacuum and the product was purified by silica gel chromatography. A chloroform/methanol (95/5) solvent was used to elute the product, yielding 382 mg of a viscous oil. Analysis on an NMR spectrometer was consistent with the desired product.

Example 14

Preparation of Mono-3-Carboxypropanamidopoly(ethylene glycol)₂₀₀ Mono-4-benzoylbenzyl Ether (Compound 21)

Compound 5, 0.500 g (1.27 mmol), prepared according to the general method described in Example 5, was dissolved in 5 ml of anhydrous chloroform along with 0.14 g (1.40 mmol) of succinic anhydride. After solution was complete, 0.141 g (1.39 mmol) of TEA were added with stirring under argon. The resulting mixture was stirred at room temperature for 24 hours. The solvent was then removed under vacuum and the product was purified on a silica gel flash chromatography column using a chloroform solvent, followed by a chloroform/methanol (95/5 to 90/10 v/v) solvent gradient. Pooling of appropriate fractions and evaporation of solvent gave 447 mg of a viscous oil. Analysis on an NMR spectrometer was consistent with the desired product.

Example 15

Preparation of Hexadecyl 4-Benzoylbenzyl Ether (Compound 22)

1-Hexadecanol, 5.0 g (20.6 mmol), was dissolved in 10 ml of anhydrous THF with warming, followed by slow addition of 0.840 g (21.0 mmol) of a 60% dispersion

of NaH in mineral oil. Once the hydrogen evolution was complete, 6.35 g (23.1 mmol) of BMBP, prepared according to the general method described in Example 2, were added. The reaction mixture was stirred at 50°C under argon for one hour and then at room temperature for 16 hours. After this time the reaction was quenched with water and the product was extracted with chloroform. After drying over sodium sulfate, the solvent was removed under vacuum and the residue was purified by silica gel flash chromatography using a hexane/ether (90/10) solvent. Appropriate fractions were pooled and evaporated to give 8.01 g of a waxy solid, an 88.9% yield. Analysis on an NMR spectrometer was consistent with the desired product.

10

Example 16

Preparation of Poly(ethylene glycol)₂₀₀ Mono-hexadecyl Mono-4-benzoylbenzyl Ether (Compound 23)

Compound 3, 1.00g (2.54 mmol), prepared according to the general method described in Example 3, was dissolved in 10 ml of anhydrous THF under an argon atmosphere. Sodium hydride, 0.112 g (2.80 mmol) of a 60% dispersion in mineral oil, was added in portions while stirring on an ice bath. The mixture was allowed to stir 20 minutes at room temperature, followed by the addition of 0.776 g (2.54 mmol) of 1-bromohexadecane. The mixture was stirred overnight at room temperature. The reaction was quenched with water and the product was extracted with chloroform. After drying over sodium sulfate and removal of solvent, the product was purified by silica gel flash chromatography using a chloroform/methanol/acetic acid/water (85/15/1/1 v/v) solvent as eluent. The appropriate fractions were pooled to give 1.357 g of product, an 86% yield. Analysis on an NMR spectrometer was consistent with the desired product.

25

Example 17

Preparation of Poly(ethylene glycol)₂₀₀ Mono-15-carboxypentadecyl Mono-4-benzoylbenzyl Ether (Compound 24)

10-Hydroxyhexadecanoic acid, 0.785 g (2.88 mmol), was dissolved in 20 ml of anhydrous DMF in a dry flask under argon. Sodium hydride, 0.260 g (6.5 mmol) of a 60% dispersion in mineral oil, was then added and the resulting slurry was stirred

30

at 60°C for four hours. After this time, Compound 4, 1.24 g (2.62 mmol), prepared according to the general method described in Example 4, was added as a solution in 7 ml of DMF. The resulting slurry was stirred at room temperature for 72 hours. After this time, the reaction was quenched with water and the product was extracted with 5 chloroform. After drying over sodium sulfate, the product was purified on a silica gel flash chromatography column. The column was eluted with chloroform/methanol (95/5 v/v) until the less polar impurities were removed, followed by elution of the product with chloroform/methanol/acetic acid/water (90/10/1/1 v/v). The appropriate fractions were pooled and evaporated to yield 1.24 g of product, a 74% yield.

10 Analysis on an NMR spectrometer was consistent with the desired product.

Example 18

Preparation of Mono-15-carboxypentadecanamidopoly(ethylene glycol)₂₀₀ Mono-4-benzoylbenzyl Ether (Compound 25)

Hexadecanedioic acid, 0.500 g (1.75 mmol), was dissolved in 5 ml of anhydrous DMF with stirring under an argon atmosphere. N-Hydroxysuccinimide, 0.442 g (3.84 mmol) and dicyclohexylcarbodiimide, 1.44 g (6.98 mmol), were added and the mixture was stirred for six hours at room temperature. The resulting solid was removed by filtration and the filter cake was washed with 1 ml of DMF. The solution was then reacted with 0.747 g (1.90 mmol) of Compound 5, prepared according to the general method described in Example 5, dissolved in 5 ml of DMF and 0.389 g (3.84 mmol) of TEA. After stirring two hours at room temperature, TLC showed complete consumption of the starting amine. The product was purified on a silica gel flash chromatography column by eluting less polar impurities using chloroform and elution of the desired product using a chloroform/methanol/acetic acid/water (85/15/1/1 v/v) solvent. The appropriate fractions were pooled and evaporated to give 1.356 g of product. Analysis on an NMR spectrometer was consistent with the desired product.

15

20

25

Example 19

Preparation of N-[3-Methacrylamido)propyl]-2-(carboxymethyl)hexadecanamide
(Compound 26) and N-[3-Methacrylamido)propyl]-3-carboxyheptadecanamide
(Compound 27)

- 5 N-(3-Aminopropyl)methacrylamide hydrochloride (APMA-HCl), 6.064 (33.9 mmol), was dissolved in anhydrous methylene chloride along with 10.24 g (101 mmol) of TEA. TDSA, 10.0 g (33.7 mmol), was immediately added and the mixture was stirred 48 hours at room temperature with moisture protection from a drying tube. After this time, the reaction was acidified with 1 N HCl, extracted with chloroform, 10 and dried over sodium sulfate. The product was purified on a silica gel chromatography column using a chloroform/methanol/acetic acid/water (85/15/1/1 v/v) solvent. The appropriate fractions were pooled, 100 ppm of phenothiazine were added, and the solvent was removed under reduced pressure to give 16.0 g of product as a pair of regioisomers resulting from opening of the anhydride ring. Analysis on an 15 NMR spectrometer was consistent with the desired products.

Example 20

Preparation of N-[3-(4-Benzoylbenzamido)propyl]methacrylamide (BBA-APMA)
(Compound 28)

- APMA-HCl, 120.0 g (0.672 mol), was suspended in 800 ml of chloroform 20 along with 25 mg of phenothiazine. The solution was cooled to below 10°C, followed by the addition of 172.5 g (0.705 mol) of BBA-Cl, prepared according to the general method described in Example 1. A solution of 150.3 g (1.49 moles) of TEA in 50 ml of chloroform was prepared and the solution was added dropwise to the above suspension over a 1-1.5 hour time period while stirring on an ice bath. After 25 completion of the addition, the ice bath was removed and the solution was stirred for 2.5 hours to complete the reaction. The mixture was then washed with 600 ml of 0.3 N HCl followed by 2 x 300 ml of 0.07 N HCl. The chloroform solution was then dried over sodium sulfate and the product was recrystallized twice using a 30 toluene/chloroform (4/1 v/v) mixture. Phenothiazine, 25 mg, was added prior to the second recrystallization to prevent premature polymerization. The yield was 212 g

(90% yield) with a melting point of 147-151°C. Analysis on an NMR spectrometer was consistent with the desired product.

Example 21

Preparation of N-(2-Mercaptoethyl)-3,5-bis(4-benzoylbenzyloxy)benzamide

5

(Compound 29)

A photoactivatable chain transfer reagent was prepared in the following manner, and used in the manner described in Examples 22 and 24. 3,5-Dihydroxybenzoic acid, 46.2 g (0.30 moles), was weighed into a 250 ml flask equipped with a Soxhlet extractor and condenser. Methanol, 48.6 ml, and
10 concentrated sulfuric acid, 0.8 ml, were added to the flask and 48 g of 3A molecular sieves were placed in the Soxhlet extractor. The extractor was diluted with methanol and the mixture was heated at reflux overnight. Gas chromatographic analysis on the resulting product showed a 98% conversion to the desired methyl ester. The solvent was removed under reduced pressure to give approximately 59 g of crude product.
15 This product was used in the following step without further purification. A small sample was purified for NMR analysis, resulting in a spectrum consistent with the desired product.

The entire methyl ester product from above was placed in a 2 liter flask with overhead stirrer and condenser, followed by the addition of 173.25 g (0.63 mol) of
20 BMBP, prepared according to the general method described in Example 2, 207 g (1.50 mol) of potassium carbonate, and 1200 ml of acetone. The resulting mixture was then refluxed overnight to give complete reaction as indicated by TLC. The solids were removed by filtration and the acetone was evaporated under reduced pressure to give 49 g of crude product. The solids were diluted with 1 liter of water and extracted with
25 3 x 1 liter of chloroform. The extracts were combined with the acetone soluble fraction and dried over sodium sulfate, yielding 177 g of crude product. The product was recrystallized from acetonitrile to give 150.2 g of a white solid, a 90% yield for the first two steps. Melting point of the product was 131.5°C (DSC) and analysis on an NMR spectrometer was consistent with the desired product.

The methyl 3,5-bis(4-benzoylbenzyloxy)benzoate, 60.05 g (0.108 mol), was placed in a 2 liter flask, followed by the addition of 120 ml of water, 480 ml of methanol, and 6.48 g (0.162 mol) of sodium hydroxide. The mixture was heated at reflux for three hours to complete hydrolysis of the ester. After cooling, the methanol
5 was removed under reduced pressure and the sodium salt of the acid was dissolved in 2400 ml of warm water. The acid was precipitated using concentrated hydrochloric acid, filtered, washed with water, and dried in a vacuum oven to give 58.2 g of a white solid (99% yield). Melting point on the product was 188.3°C (DSC) and analysis on an NMR spectrometer was consistent with the desired product.

10 The 3,5-bis(4-benzoylbenzyloxy)benzoic acid, 20.0 g (36.86 mmol), was added to a 250 ml flask, followed by 36 ml of toluene, 5.4 ml (74.0 mmol) of thionyl chloride, and 28 µl of DMF. The mixture was refluxed for four hours to form the acid chloride. After cooling, the solvent and excess thionyl chloride were removed under reduced pressure. Residual thionyl chloride was removed by four additional
15 evaporations using 20 ml of chloroform each. The crude material was recrystallized from toluene to give 18.45 g of product, an 89% yield. Melting point of product was 126.9°C (DSC) and analysis on an NMR spectrometer was consistent with the desired product.

The 2-aminoethanethiol hydrochloride, 4.19 g (36.7 mmol), was added to a
20 250 ml flask equipped with an overhead stirrer, followed by 15 ml of chloroform and 10.64 ml (76.5 mmol) of TEA. After cooling the amine solution on an ice bath, a solution of 3,5-bis(4-benzoylbenzyloxy)benzoyl chloride, 18.4 g (32.8 mmol), in 50 ml of chloroform was added dropwise over a 50 minute period. Cooling on ice was continued 30 minutes, followed by warming to room temperature for two hours. The
25 product was diluted with 150 ml of chloroform and washed with 5 x 250 ml of 0.1 N hydrochloric acid. The product was dried over sodium sulfate and recrystallized twice from toluene/hexane (15/1 v/v) to give 13.3 g of product, a 67% yield. Melting point on the product was 115.9°C (DSC) and analysis on an NMR spectrometer was consistent with the desired product.

Example 22

Preparation of a Photoreactive Endpoint Copolymer of Acrylamide and Fatty Acid
Monomers (Compound 30)

Acrylamide, 0.640 g (9.00 mmol), was dissolved in 9 ml of THF, followed by
5 the addition of 0.299 g (0.68 mmol) of Compounds 26 and 27, prepared according to
the general method described in Example 19, 0.060 g (0.10 mmol) of Compound 29,
prepared according to the general method described in Example 21, 9 μ l (0.060 mmol)
of N,N,N',N'-tetramethylethylenediamine (TEMED), and 0.049 g (0.30 mmol) of
2,2'-azobisisobutyronitrile (AIBN). The solution was sparged two minutes with
10 helium, two minutes with argon, and was then sealed and heated overnight at 55°C.
The resulting suspension was diluted with 5 ml of additional THF and added to
diethyl ether, followed by filtration to isolate the solid. After drying in a vacuum
oven, 0.966 g of a white solid were isolated. Analysis of the polymer revealed 0.073
mmol of BBA per gram of polymer.

15

Example 23

Preparation of a Photoreactive Random Copolymer of Acrylamide and Fatty Acid
Monomers (Compound 31)

Acrylamide, 0.657 g (9.24 mmol), was dissolved in 9 ml of THF, followed by
the addition of 0.307 g (0.70 mmol) of Compounds 26 and 27, prepared according to
20 the general method described in Example 19, 0.036 g (0.10 mmol) of Compound 28,
prepared according to the general method described in Example 20, 9 μ l (0.060 mmol)
of TEMED, and 0.026 g (0.16 mmol) of AIBN. The solution was sparged two
minutes with helium, two minutes with argon, and was then sealed and heated
overnight at 55°C. The resulting suspension was diluted with 5 ml of additional THF
25 and added to diethyl ether, followed by filtration to isolate the solid. After drying in a
vacuum oven, 0.997 g of a white solid were isolated. Analysis of the polymer
revealed 0.086 mmol of BBA per gram of polymer.

Example 24

Preparation of a Photoreactive Endpoint Copolymer of N-Vinylpyrrolidone and Fatty Acid Monomers (Compounds 32A-C)

- N-Vinylpyrrolidone, 0.915 g (8.23 mmol), was dissolved in 3 ml of THF, followed by the addition of 0.271 g (0.618 mmol) of Compounds 26 and 27, prepared according to the general method described in Example 19, 0.070 g (0.116 mmol) of Compound 29, prepared according to the general method described in Example 21, 1 μ l (0.01 mmol) of TEMED, and 0.057 g (0.347 mmol) of AIBN. This composition was designed to make TDSA 7 mole % of the monomers in the reaction mixture. The solution was sparged two minutes with helium, two minutes with argon, and was then sealed and heated overnight at 55°C. The polymer was precipitated by the addition of diethyl ether, followed by isolation with filtration. After drying in a vacuum oven, 1.10 g of a white solid were isolated. Analysis of Compound 32A revealed 0.109 mmol of BBA per gram of polymer.
- The above procedure was followed using the following quantities of reagents in 4 ml of THF: N-vinylpyrrolidone, 0.433 g (3.90 mmol); Compounds 26 and 27, 0.507 g (1.16 mmol) Compound 29, 0.060 g (0.10 mmol); TEMED, 3 μ l (0.02 mmol); and AIBN, 0.049 g (0.298 mmol). This composition was designed to make TDSA 23 mole % of the monomers in the reaction mixture. After isolation following the above procedure, 0.808 g of a white solid were isolated. Analysis of Compound 32B revealed 0.083 mmol of BBA per gram of polymer.

- The above procedure was followed using the following quantities of reagents in 3 ml of THF: N-vinylpyrrolidone, 0.181 g (1.63 mmol); Compounds 26 and 27, 0.759 g (1.73 mmol); Compound 29, 0.060 g (0.10 mmol); TEMED, 1 μ l (0.01 mmol); and AIBN, 0.049 g (0.298 mmol). This composition was designed to make TDSA 50 mole % of the monomers in the reaction mixture. After isolation following the above procedure, 0.705 g of a white solid were isolated. Analysis of Compound 32C revealed 0.102 mmol of BBA per gram of polymer.

Example 25

Preparation of a Photoreactive Random Copolymer of N-Vinylpyrrolidone and Fatty Acid Monomers (Compounds 33A-D)

N-Vinylpyrrolidone, 0.749 g (6.74 mmol), was dissolved in 8.8 ml of THF, followed by the addition of 0.224 g (0.511 mmol) of Compounds 26 and 27, prepared according to the general method described in Example 19, 0.027 g (0.077 mmol) of Compound 28, prepared according to the general method described in Example 20, 1 μ l (0.01 mmol) of TEMED, and 0.019 g (0.116 mmol) AIBN. This composition was designed to make TDSA 7 mole % of the monomers in the reaction mixture. The solution was sparged two minutes with helium, two minutes with argon, and was then sealed and heated overnight at 55°C. The polymer was precipitated by the addition of diethyl ether, followed by isolation with filtration. After drying in a vacuum oven, 0.353 g of a white solid were isolated. Analysis of the Compound 33A revealed 0.112 mmol of BBA per gram of polymer.

The above procedure was followed using the following quantities of reagents in 3 ml of THF: N-vinylpyrrolidone, 0.362 g (3.26 mmol); Compounds 26 and 27, 0.621 g (1.42 mmol); Compound 28, 0.017 g (0.049 mmol); TEMED, 1 μ l (0.01 mmol); and AIBN, 0.012 g (0.073 mmol). This composition was designed to make TDSA 30 mole % of the monomers in the reaction mixture. After isolation following the above procedure, 0.770 g of a white solid were isolated. Analysis of Compound 33B revealed 0.052 mmol of BBA per gram of polymer.

The above procedure was followed using the following quantities of reagents in 3 ml of THF: N-vinylpyrrolidone, 0.196 g (1.76 mmol); Compounds 26 and 27, 0.791 g (1.80 mmol); Compound 28, 0.013 g (0.037 mmol); TEMED, 1 μ l (0.01 mmol); and AIBN, 0.009 g (0.055 mmol). This composition was designed to make TDSA 50 mole % of the monomers in the reaction mixture. After isolation following the above procedure, 0.708 g of a white solid were isolated. Analysis of Compound 33C revealed 0.048 mmol of BBA per gram of polymer.

The above procedure was followed using the following quantities of reagents in 7 ml of THF: N-vinylpyrrolidone, 0.188 g (1.69 mmol); Compounds 26 and 27,

1.792 g (4.09 mmol); Compound 28, 0.020 g (0.057 mmol); TEMED, 1 μ l (0.01 mmol); and AIBN, 0.014 g (0.085 mmol). This composition was designed to make TDSA 70 mole % of the monomers in the reaction mixture. After isolation following the above procedure, 0.879 g of a white solid were isolated. Analysis of Compound 5 33D revealed 0.058 mmol of BBA per gram of polymer.

Example 26

Preparation of a Photoreactive Siloxane Copolymer Containing Fatty Acid Ligands (Compound 34)

An aminopropylmethylsiloxane-dimethylsiloxane copolymer, 5.00 g of a 6-7 mole % amine monomer content, was dissolved in 50 ml of dry methylene chloride, followed by the addition of 0.79 g (7.81 mmol) of TEA. BBA-Cl, 0.19 g (0.78 mmol), prepared according to the general method described in Example 1, was then added and the mixture was stirred 3 hours at room temperature. TDSA, 0.924 g (3.12 mmol), was then added and the solution was stirred 24 hours at room temperature. The reaction was then diluted with water and the pH was adjusted to approximately 6 using 0.1 N HCl. The organic layer was removed and dried over sodium sulfate. The solvent was removed under reduced pressure and the resulting oil was diluted with hexane. The precipitate was removed by filtration and evaporation of the solvent gave 4.75 g of a viscous oil. Analysis of the polymer revealed 0.013 mmol of BBA per gram of polymer.

Example 27

Fatty Acid Immobilization on an Amine Derivatized Surface

A polymer surface is derivatized by plasma treatment using a 3/1 mixture of methane and ammonia gases (v/v). (See, e.g., the general method described in U.S. Patent 5,643,580). A mixture of methane (490 SCCM) and ammonia (161 SCCM) are introduced into the plasma chamber along with the polymer part to be coated. The gases are maintained at a pressure of 0.2-0.3 torr and a 300-500 watt glow discharge is established within the chamber. The sample is treated for a total of 3-5 minutes under these conditions. Formation of an amine derivatized surface is verified by surface

analysis using Electron Spectroscopy for Chemical Analysis (ESCA) and Time of Flight Secondary Ion Mass Spectrometry (TOF-SIMS).

TDSA is dissolved at a concentration of 30 mg/ml in a solvent compatible with both the polymer substrate and the anhydride. TEA, 1.5 equivalents relative to the anhydride, are added to the solution and the final mixture is allowed to incubate with the amine derivatized surface for 24 hours at room temperature to permit maximal coupling of the fatty acid to the surface. The final surface is then washed with fresh solvent to remove all unreacted materials and the final wash is a dilute acid wash to remove any remaining TEA.

Example 28

Surface modification of selected substrates with reagents

Three polymers commonly-used as biomaterials were surface-modified with novel compounds described above. The polymer substrates included polyethylene (PE), polyvinylchloride (PVC), and polyurethane (PU). These polymers were obtained as flat sheets and used as 1 × 1 cm squares, 1 cm circular disks or obtained in cylindrical form (tubes or rods) and used as short segments. The shape and size of the part was chosen based on the particular assay to be conducted with the coated substrates.

Coating solutions were prepared by dissolving the reagents at concentrations ranging from 1-15 mg/ml in neat isopropanol (IPA) or deionized water/IPA solutions. The reagents were applied to the polymer substrates using dip coating methods. Parts were suspended vertically, immersed in the solution at 2 cm/sec, allowed to dwell for five seconds, and then withdrawn at a rate of 0.1 cm/sec. After removal of the substrate from the coating solution, it was air dried until the solvent was no longer visible, often within about 1 minute. The substrate with the coating was then suspended midway between two opposed Dymax UV curing lamps, each outfitted with a Heraeus Q402Z4 bulb. At the distance of placement of the lamps, the parts received approximately 1.5 mW/cm² in the wavelength range 330-340 nm. The substrate was rotated at 3 rpm during the two minutes of illumination to ensure that the surface was evenly bathed in light. After illumination, the parts were removed from the lamp chamber and washed in IPA, using two sequential 30-minute washes in

fresh solvent. The coated samples were then stored in the dark at ambient temperature until used.

Example 29

5 Surface Analysis of Polymer Substrates Modified with Compounds

8, 9, 18, 19, 32, and 33.

Three different techniques (staining, ESCA, and TOF-SIMS) were used to evaluate the surfaces of modified substrates to confirm the presence and uniformity of the compounds.

10 PE and PVC flat materials were modified with heterobifunctional reagents (Compounds 8, 9, 18, 19) and polymeric reagents (Compounds 32 and 33, having varying monomer compositions). Reagents were prepared in IPA at 1.0 mg/ml and applied using the methods described in Example 28.

15 First, the coated materials were stained with Toluidine Blue O, a positively-charged, visible-wavelength dye. Samples were immersed in a solution of the dye (0.02% w/v in water) for 30 seconds, removed from solution, and rinsed with DI water. This staining protocol was useful for identifying qualitatively the presence of each of the reagents on the material surface. The results of the dye binding suggested that the surface modification procedures were successful in immobilizing the reagents
20 on the substrate surfaces. There was some variability in the darkness of the stain, both from different reagents on the same material and for the same reagents on different materials. The staining was grossly uniform to the naked eye over the surfaces of the material, suggesting that the reagent was not pooling or segregating when applied to the surface and that the coverage of the surface was relatively uniform.

25 ESCA was used to analyze quantitatively the surface chemical composition of the modified substrates. PE and PVC modified with heterobifunctional reagents (Compounds 8, 9, 18, 19) and polymeric reagents (Compounds 32 and 33, having varying molar compositions) were analyzed with a Perkin Elmer Model 5400 ESCA system using monochromatic Al X-rays with analysis at a 65 degree takeoff angle.

30 Survey spectra were collected to calculate the atomic concentrations in the surface.

The results of the ESCA measurements (Tables 1 and 2) on the surface modified materials were useful for indicating the presence and chemical composition of the coatings. For the PVC substrate, the atomic concentration of the chlorine atom (Cl) was used to determine whether the coating masked the substrate material. By comparing the amounts of Cl detected on the surface of the PVC after modification, it was clear that the Cl was greatly reduced on the surface-modified substrates. Together with the results of the dye binding described above, this suggested that the reagents covered the surface completely, but were thin enough to detect the underlying substrate. For the PE substrate, which in the uncoated state should have an atomic concentration of 100% carbon (as ESCA cannot detect H atoms), the modified and unmodified samples could simply be compared using the carbon concentration. On all of the modified samples the carbon concentration was reduced by about 20%. It was also evident that nitrogen was present on the surfaces of the modified PE and PVC, but not on the uncoated surfaces. This was indicative of the nitrogen in each of the reagents. Finally, the similarity in the atomic concentrations of C, O, and N on the surfaces of PE and PVC samples modified with each compound supports the presence and completeness of the coating.

Table 1. Atomic Concentration summary for PE samples (atomic %).

Sample	[C]	[O]	[N]	[Cl]	[Si]	[Na]
Uncoated	100	-	-	-	-	-
Compound 33D	83.4	10.5	6.2	-	-	-
Compound 33C	80.9	11.3	7.8	-	-	-
Compound 33B	80.7	11.1	8.3	-	-	-
Compound 32C	80.3	12.4	7.3	-	-	-
Compound 32B	79.3	12.1	8.1	-	0.5	-
Compounds 18, 19	83.8	13.9	2.3	-	-	-
Compounds 8, 9	81.4	16.8	1.6	-	-	0.2

Table 2. Atomic Concentration Summary for PVC samples (atomic %).

Sample	[C]	[O]	[N]	[Cl]	[Si]	[Na]
Uncoated	74.2	7.5	--	17.6	--	0.5
Compound 33D	80.4	11.5	6.2	1.9	--	--
Compound 33C	78.8	12.1	8.8	0.4	--	--
Compound 33B	77.8	11.6	9.1	1.3	--	0.1
Compound 32C	79.9	12.4	6.8	0.8	--	--
Compound 32B	77.6	12.2	9.1	0.4	0.7	--
Compounds 18, 19	83.4	12.8	2.4	1.4	--	--
Compounds 8, 9	79.7	17.4	1.4	1.1	--	0.3

TOF-SIMS was conducted to ensure that the coatings were located on the outermost surface of the substrates. TOF-SIMS is sensitive to the chemical structure within the outer 10 Å of a surface. TOF-SIMS was performed by Physical Electronics (Eden Prairie, MN) using a Physical Electronics model number 7200 instrument. Positive- and negative-ion spectra were recorded for each of the surfaces. In addition, scans of the surface were used to determine the uniformity of chemical fragments which were indicative of the coatings (independent of the substrate chemistry). The surfaces (substrates and coatings) analyzed by TOF-SIMS were the same as those analyzed by ESCA, described above. For the coated substrates, the TOF-SIMS spectra were substantially different from the spectra for the uncoated PE or PVC material. For example, there were many chemical fragments containing nitrogen, which is not present in either of the base materials. There were many high molecular weight fragments in the positive ion spectra (between 200 and 600 mass/charge units) associated with the heterobifunctional reagents (Compounds 8, 9 and 18, 19). The polymer-based reagents (Compounds 32, 33) had regular repeating fragment fingerprints indicative of the polymer backbone. Also confirming that the reagents were present on the surfaces of the materials, was that the fragment patterns for each compound were similar on the two different substrates. In addition, the scans of the surface to detect the presence of peaks uniquely associated with the coating reagents

indicated that the reagents were relatively uniformly distributed over the surface of the substrate, further confirming the results of the Toluidine Blue O staining tests described previously.

Example 30

5 Human Serum Albumin (HSA) Adsorption from Buffer and Platelet Poor Plasma

Adsorption of human serum albumin (HSA) from single protein buffer solution and from diluted human platelet poor plasma (PPP) onto the polymer materials was quantified using radiolabeled protein. Fatty acid-free HSA (Sigma Chemical, St. Louis MO) was radiolabeled with ^3H using sodium borohydride techniques (Means and Feeney, Biochemistry 7, 2192 (1968)). Buffer solutions of HSA were prepared by dissolving unlabeled HSA to a concentration of 0.1 mg/ml in Tris-saline (TN) buffer solution (50 mM Tris, 150 mM NaCl, pH 7.5). The resulting solution was then spiked with an aliquot of the ^3H -HSA such that the specific activity was approximately 1000 dpm/ μg HSA for the total solution. Plasma solutions were prepared using a commercially-available PPP (George King Biomedical; Overland Park, KS) prepared from blood anticoagulated with sodium citrate (3.8%). Just prior to an adsorption experiment, the PPP was diluted 4:1 with phosphate buffered saline (10 mM phosphate, 150 mM NaCl, pH 7.4; PBS) and then spiked with the radiolabeled HSA such that the specific activity was approximately 6000 dpm/ μg of HSA in the diluted plasma.

Adsorption experiments were conducted identically for both the buffer and PPP solutions containing ^3H -HSA. Circular disks (1 cm) of the surface-modified PE and PVC were placed in 20 ml scintillation vials; uncoated disks of the same materials were used as controls. The pieces were hydrated in 2 ml of TN overnight at room temperature. On the day of the experiment, ^3H -HSA solutions (buffer or PPP) were prepared as described above. The hydration buffer was aspirated from the polymer samples and 1.0 ml of the radiolabeled HSA solution was added to the vial. The vials were gently agitated on an orbital shaker for 2 hours at room temperature. The HSA solution was aspirated and 4 ml of TNT solution (50 mM Tris, 150 mM NaCl, 0.05% Tween20, pH 7.5) were added to each vial; the vials were shaken for 15 minutes at

room temperature. The TNT wash step was repeated two times and the disks were transferred to clean, dry scintillation vials. Two ml of THF were added to each vial and the samples were strongly agitated on an orbital shaker overnight. To each vial, 10 ml of Hionic Fluor were added and thoroughly mixed by vortexing. The vials were counted using a liquid scintillation counter (Packard 1900 CA). The surface concentration of HSA was calculated from these data using the specific activity of the HSA adsorption solution and the surface area of the disks.

PE and PVC were modified with heterobifunctional and polymeric compounds using the same procedures as described in Example 28. The results of the binding of ^3H -HSA out of TN buffer solution onto the modified and uncoated PE and PVC materials are shown in Table 3.

Table 3. Adsorption of HSA from TN buffer onto modified PE and PVC surfaces

Surface	Surface concentration of HSA ($\mu\text{g}/\text{cm}^2$)	
	PE	PVC
Uncoated	0.069 ± 0.001	0.066 ± 0.000
Compound 32B	0.068 ± 0.001	0.051 ± 0.001
Compound 32C	0.050 ± 0.001	0.036 ± 0.001
Compound 33B	0.071 ± 0.002	0.066 ± 0.001
Compound 33C	0.054 ± 0.000	0.045 ± 0.006
Compound 33D	0.136 ± 0.000	0.036 ± 0.005
Compounds 18, 19	0.128 ± 0.005	0.098 ± 0.006
Compounds 10, 11	0.167 ± 0.006	0.168 ± 0.007
Compounds 14, 15	0.191 ± 0.001	0.200 ± 0.010
Compound 8, 9	0.191 ± 0.010	0.159 ± 0.007

The results of HSA binding from buffer solution indicated that many of the polymeric reagents bound HSA at similar levels to uncoated surfaces, whereas the heterobifunctional compounds enhanced binding by 2- to 3-fold over uncoated.

Example 31

HSA binding from plasma to PE modified with Compounds 8, 9, 18, 19, 30, 32, and 33

PE flat substrates were modified with Compounds 8, 9, 18, 19, 30, 32, and 33.

- 5 Compounds 8, 9, 18, 19, 32, and 33 were prepared in IPA at concentration of 1 mg/ml and Compound 30 was prepared in IPA/water (80/20 v/v), and substrates were coated following the procedure as described in Example 28. HSA binding from PPP was measured as described in Example 30; the specific activity was 2,003 dpm/ μ g.

Table 4.

10 HSA binding from PPP onto PE

Surface (PE)	Surface concentration (μ g/cm ²)
Uncoated	0.008 \pm 0.001
Compound 32B	0.064 \pm 0.012
Compound 33A	0.010 \pm 0.000
Compound 33B	0.168 \pm 0.002
Compound 30	0.015 \pm 0.000
Compounds 18, 19	0.017 \pm 0.002
Compounds 8, 9	0.012 \pm 0.001

Example 32

HSA binding from plasma to PVC modified with Compounds 8, 9, 32, and 33

PVC flat substrates were modified with Compounds 8, 9, 32, and 33. The

- 15 compounds were prepared in IPA at concentration of 1 mg/ml, and were applied to the substrates following the procedure as described in Example 28. HSA binding from PPP was measured as described in Example 30; in this experiment the specific activity was 3,150 dpm/ μ g HSA.

Table 5.

HSA binding from PPP onto PVC.

Surface	Surface concentration ($\mu\text{g}/\text{cm}^2$)
Uncoated	0.0183 ± 0.0005
Compound 32C	0.0460 ± 0.0040
Compound 32B	0.0420 ± 0.0010
Compound 33C	0.1720 ± 0.0120
Compound 33B	0.0830 ± 0.0020
Compounds 8, 9	0.0296 ± 0.0010

Example 33

5

HSA binding from plasma to PE modified with Compounds 14, 15

PE flat substrates were modified with Compounds 14, 15. The compounds were prepared in IPA at concentrations ranging from 1-10 mg/ml and applied as one coat or three coats, otherwise following the procedure as described in Example 28.

HSA binding from PPP was measured as described in Example 30; specific activity of

10 HSA was 5,636 dpm/ μg in experiment #1 and #2. The results are shown in Table 6.

Table 6.

HSA binding from PPP onto PE modified with Compounds 14, 15

Surface	Surface concentration of HSA ($\mu\text{g}/\text{cm}^2$)	
	Experiment #1	Experiment #2
Uncoated PE	0.14 ± 0.004	0.12 ± 0.005
1 mg/ml (3 coats)	0.16 ± 0.008	n.d.*
2.5 mg/ml (3 coats)	0.28 ± 0.011	n.d.
5 mg/ml (1 coat)	n.d.	0.48 ± 0.014
5 mg/ml (3 coats)	0.48 ± 0.016	1.22 ± 0.046
7.5 mg/ml (1 coat)	n.d.	0.67 ± 0.024
7.5 mg/ml (3 coats)	0.91 ± 0.018	1.02 ± 0.053
10 mg/ml (1 coat)	n.d.	0.52 ± 0.012
10 mg/ml (3 coats)	0.70 ± 0.037	1.18 ± 0.111

*n.d. is not determined

The results of this experiment indicate that increasing the concentration of applied reagent yields surfaces which show increased binding of HSA from PPP. In addition, increasing the number of coats of reagent applied to the surface yields increased binding of HSA from PPP.

Example 34

HSA binding from plasma to PE modified with Compounds 10, 11

PE flat substrates were modified with Compounds 10, 11. The compounds were prepared in IPA at concentrations ranging from 1-15 mg/ml and applied in three coats, otherwise following the procedure as described in Example 28. HSA binding from PPP was measured as described in Example 30; specific activity of the HSA in plasma was 5,977 dpm/ μ g in Experiment #1 and 6,636 dpm/ μ g in Experiment #2.

Table 7.

HSA binding from PPP onto PE modified with Compounds 10, 11

Surface	Surface concentration of HSA (μ g/cm ²)	
	Experiment #1	Experiment #2
Uncoated PE	0.19 \pm 0.024	0.22 \pm 0.017
1 mg/ml	0.43 \pm 0.026	n.d.
2.5 mg/ml	0.25 \pm 0.016	n.d.
5 mg/ml	0.64 \pm 0.030	n.d.
7.5 mg/ml	0.76 \pm 0.084	n.d.
10 mg/ml	1.04 \pm 0.076	1.26 \pm 0.092
12.5 mg/ml	n.d.	0.91 \pm 0.047
15 mg/ml	n.d.	1.02 \pm 0.052

15

The results of this experiment indicate that increasing the concentration of applied reagent yields increased HSA binding, although it appears as though the HSA binding reaches a plateau where further increases in the reagent applied to the surface provide no additional benefit. This may indicate that the surface has become saturated with reagent.

20

Example 35

HSA Binding to PE Modified with Compounds 8, 9

PE flat substrates were modified with Compounds 8, 9. The compounds were prepared in IPA at concentrations ranging from 1-10 mg/ml and applied as one coat or
 5 three coats, otherwise following the procedure as described in Example 28. HSA binding from PPP was measured as described in Example 30; specific activity in plasma was 6,045 dpm/ μ g HSA.

Table 8.

HSA binding from PPP onto PE modified with Compounds 8, 9.

10

Surface	Surface concentration of HSA (μ g/cm ²)	
	One coat	Three coats
Uncoated PE	0.196 \pm 0.034	n.a.
1 mg/ml	0.194 \pm 0.021	0.309 \pm 0.039
2.5 mg/ml	0.3403 \pm 0.034	0.642 \pm 0.069
5 mg/ml	0.627 \pm 0.067	0.692 \pm 0.024
7.5 mg/ml	1.043 \pm 0.083	0.873 \pm 0.063
10 mg/ml	1.071 \pm 0.197	1.067 \pm 0.013

These coatings on PE and PVC enhanced HSA binding from buffer and plasma by as much as 10-fold. With some reagents (10, 11, 14, 15, and 8, 9), increasing concentration of coating solution produced surfaces with increasing
 15 capacity to bind HSA. This plateau occurred near 7.5 mg/ml for reagent 14, 15. For Compounds 8, 9, 10, 11, this plateau occurred near 10 mg/ml.

Example 36

Fibrinogen (Fgn) Adsorption from PPP onto Modified Substrates

PE and PVC substrates were modified with Compounds 8, 9, 18, 19, 32, and
 20 33. The compounds were prepared in IPA at a concentration of 1.0 mg/ml and applied as a single coat, otherwise following the procedure as described in Example 28.

Adsorption of Fgn from human plasma (PPP) onto the control and surface-modified materials was quantified by using ^3H -Fgn. Fgn was radiolabeled with ^3H using sodium borohydride techniques (Means and Feeney, *Biochemistry* 7, 2192 (1968)) and stored frozen at -80°C until used. Plasma solutions of Fgn for adsorption experiments were prepared using PPP (George King Biomedical; Overland Park, KS). On the day of the adsorption experiment, PPP was diluted 4:1 with TN buffer. The diluted PPP was then spiked with an aliquot of the stock ^3H -Fgn solution to give a working solution with specific activity 1,816 dpm/ μg Fgn.

Polymer samples (1 cm circular disks) were placed in 20 ml scintillation vials and hydrated overnight in 2.0 ml of TN at room temperature prior to protein adsorption. On the day of the experiment, the buffer solution was aspirated and 1.0 ml of the diluted PPP containing the ^3H -Fgn was added to completely cover the polymer sample. The substrates were incubated in the ^3H -Fgn solution for 2 hours at 23°C . The PPP solution was aspirated and the substrates washed three times with TNT (15 minutes each time). Disks were placed in clean scintillation vials, dissolved with THF, and counted for radioactivity as described in Example 30 for the HSA adsorption experiments. Surface concentrations of Fgn were calculated using the specific activity of the Fgn in the solution and the surface area of the polymer samples. The experimental results of the fibrinogen adsorption experiments are shown in Table 10.

Table 10.

Fgn adsorption to PE and PVC modified with Compounds 8, 9, 18, 19, 32, and 33

Surface treatment	Surface concentration of Fgn ($\mu\text{g}/\text{cm}^2$)	
	PE	PVC
Uncoated	0.231 ± 0.152	0.269 ± 0.060
Compound 33C	0.148 ± 0.044	0.092 ± 0.003
Compound 33B	0.160 ± 0.013	0.112 ± 0.013
Compound 32C	0.129 ± 0.016	0.180 ± 0.005
Compound 32B	0.167 ± 0.016	0.249 ± 0.018
Compounds 18, 19	0.131 ± 0.051	0.193 ± 0.029
Compounds 8, 9	0.194 ± 0.032	0.222 ± 0.062

With these reagents, Fgn binding to modified surfaces was equal to or less than adsorption to uncoated surfaces. It is possible that the enhanced binding of HSA was responsible for reduced binding of Fgn. Surfaces that reduce the binding of Fgn are generally less likely to induce subsequent unfavorable responses from blood, such as fibrin formation and platelet adhesion.

Example 37

Binding of Anti-HSA Antibodies to Modified PE Exposed to HSA

PE substrates were modified with Compounds 8, 9, 18, 19, 30, 31, 32, and 33. The compounds were prepared in IPA at a concentration of 1.0 mg/ml and applied as a single coat, otherwise following the procedure as described in Example 28.

The binding of polyclonal anti-HSA antibodies was conducted using an ELISA technique to determine whether bound albumin maintained native structure in the absorbed state. Sheep anti-(HSA) antibodies conjugated to horseradish peroxidase (HRP) were obtained from Biodesign (Kennebunk, ME). Polymer samples were hydrated with TN for 2 hours, and the protein solution was prepared with an HSA concentration of 1.0 mg/ml in TN. 1 ml of the protein solution was added to the samples and incubated for 2 hours at room temperature. After the adsorption, the solution was aspirated and the samples rinsed with TNT buffer. 1 ml of 1% BSA was added as a blocking step and incubated for one hour. The samples were washed twice with TNT for 30 min. each. After the wash, the samples were briefly rinsed with TN and incubated with the sheep-Ab-HRP in TN (diluted 1:2000), at room temperature for 1 hour with gentle agitation. The samples were washed 4 times with 3 mls TNT per vial by vortex. The pieces were transferred to test tubes and 1 ml TMB/peroxide solution was added. The color was allowed to develop for 15 minutes. The absorbance of the solutions was read at 655 nm using a spectrophotometer. The absorbance is directly proportional to the surface concentration of HRP and, therefore, also proportional to the surface concentration of anti-HSA antibody bound to the substrate surfaces.

Table 11.

Results of anti-albumin antibody binding to HSA exposed surface

Surface	Bound Ab (A_{655})
Uncoated	0.134 ± 0.005
Compound 32A	0.354 ± 0.030
Compound 32B	0.335 ± 0.022
Compound 32C	0.338 ± 0.017
Compound 33A	0.311 ± 0.026
Compound 33B	0.385 ± 0.034
Compound 33C	0.352 ± 0.020
Compound 30	0.332 ± 0.016
Compound 31	0.289 ± 0.025
Compounds 8, 9	0.456 ± 0.016
Compounds 18, 19	0.488 ± 0.020

The results of anti-HSA antibody binding to HSA previously absorbed from buffer to the uncoated and surface-modified materials indicated that there was little difference among the reagents tested. All surfaces bound high concentrations of antibody, about 3 to 4-fold higher than uncoated surfaces.

Example 38

Platelet Attachment and Activation from Platelet Rich Plasma (PRP) on Modified PE and PVC

The surface-modified materials were incubated with platelet rich plasma (PRP) and then examined with a scanning electron microscope (SEM) to determine the influence of surface chemistry on platelet attachment and activation. Blood was collected fresh from human volunteers into 3.8% sodium citrate using 9:1 ratio of blood to anticoagulant. The blood was centrifuged at 1200 rpm for 15 min. to separate PRP from blood. The PRP was collected and kept at room temperature until used (less than 1 hour). The test samples (1 inch squares) were placed in a 6-well plate, 1 sample per well. To quantify the platelets in the plasma, a sample of the PRP

was taken and diluted 1:100 with 1% ammonium oxalate. A capillary tube was used to transfer a small amount of solution to a hemacytometer, and the sample was incubated in a covered petri dish for 30 minutes for the platelets to settle. The platelets were counted under a phase contrast microscope and determined to be between $1.4 - 4.4 \times 10^{14}$ platelets/ml. The PRP solution was added onto the top of the samples until the entire surface was covered, and the samples were incubated one hour at room temperature with no agitation. After incubation, the PRP was removed carefully by aspiration and 3 mls of Tyrode's buffer (138 mM NaCl, 2.9 mM KCl, 12 mM sodium bicarbonate, pH 7.4) was gently added to each well. The plates were agitated slightly on an orbital shaker for 15 min.; the solution was changed and the wash repeated. The wash solution was aspirated and 2.0 ml of Karnovsky's fixative (25 mls formaldehyde + 5 mls 25% glutaraldehyde + 20 mls of a solution of 23% $\text{NaH}_2\text{PO}_4 \cdot \text{H}_2\text{O}$ + 77% NaHPO_4 anhydrous) were added to each well. The plate was wrapped with parafilm and incubated overnight with slight agitation. The fixative was aspirated and the samples were washed three times each with pure water, 15 minutes for each wash. The samples were then dehydrated with an ethanol series of 25, 50, 75, and 100%, for 15 minutes each. The samples were kept at 4°C in 100% ethanol until mounted (up to 4 days). Samples were mounted and coated with Pd/Au and observed using a JEOL 840 scanning electron microscope. Photos were taken of different areas on the sample surface at several magnifications to give a representative view of each sample. The platelets were counted and judged for degree of activation using morphological descriptions based on Goodman et al Scanning Electron Microscopy/1984/I, 279-290 (1984).

The SEM results for two representative platelet attachment experiments are shown in Tables 12 and 13. From the SEM photographs, surface densities of bound platelets were estimated. The lowest platelet densities were found on the Compound 33C polymer consistently on both substrates. The Compound 32C polymer also had low platelet densities consistently. The predominant platelet morphologies are summarized in Table 13. Platelets that were rounded or dendritic were interpreted to be less activated; whereas the platelets that were spreading or fully spread and showed

substantial aggregation were interpreted to be more extensively activated. For PE, the uncoated substrate had the highest platelet densities as well as the most fully spread platelet morphology. For PVC, the uncoated surface was poor but not the worst surface.

Table 12. Platelet Densities on modified surfaces (platelets/cm² x 10⁻⁶).

Reagent	PE	PVC
Uncoated	980 ± 50	650 ± 0
Compound 32C	420 ± 0	400 ± 30
Compound 33C	220 ± 5	200 ± 30
Compounds 18, 19	900 ± 30	1000 ± 200
Compounds 8, 9	400 ± 40	400 ± 0

Table 13. Morphology of platelets attached to modified surfaces.

Surface	PE	PVC
Compound 32B	Few aggregates, platelets mostly round or dendritic	N/A
Compound 32C	Some aggregates, platelets mostly round or dendritic	Few aggregates, platelets mostly round or dendritic
Compound 33C	Few aggregates, platelets mostly round or dendritic	No aggregates, platelets mostly round
Compound 33D	Few aggregates, platelets mostly round or dendritic	Some aggregates, platelets dendritic or spread dendritic
Compounds 18, 19	Many aggregates, most platelets spread or fully spread	Many aggregates, most platelets spreading or fully spread
Compounds 8, 9	Many aggregates, most platelets spread or fully spread	Few aggregates, most platelets are spreading
Uncoated	Many aggregates, most platelets are fully spread	Few aggregates, platelets are spread dendritic or fully spread

The polymeric reagents performed the best at reducing platelet attachment and activation on both substrates. The heterobifunctional reagents 8 and 9 performed similarly to the polymeric reagent 32C. The heterobifunctional reagents 18 and 19 were similar to or worse than the uncoated surface, depending on the substrate.

5

Example 39

Acute Dog Jugular Vein Implants with Catheters Modified with Compounds 6, 7

Surfaces modified with Compounds 6, 7 were tested using an acute, dog, jugular vein implant model. Surface-modified and control samples were implanted for one hour in the external jugular veins of 15-25 kg mixed-breed dogs. Attachment of ¹¹¹In-labeled, autologous platelets was monitored spatially and quantitatively in real time using gamma camera imaging.

In each experiment, the dog was anesthetized with pentobarbital and secured in a supine position. No anticoagulant was given to the animals prior to or during the experiments. Ninety ml of blood was drawn into citrate/dextrose (9:1 v/v) and the platelets were isolated and labeled with ¹¹¹In-oxine. The labeled platelets were reinfused into the dog and allowed to circulate for 20 minutes. In quick succession, one rod modified with a fatty acid derivative and one uncoated control rod were implanted bilaterally in the left and right external jugular veins. By using an uncoated control rod in each experiment, any variability in the response of individual animals to the implanted materials was accounted for. Immediately after insertion of the rods, the neck region of the dog was monitored continuously for one hour with a Picker 4/15 digital gamma camera to follow in real time the attachment of platelets onto the rods. The gamma camera allowed both digital quantification and spatial resolution of the radioactive counts. The data collected with the camera was transferred to a dedicated microcomputer to calculate the relative platelet adhesion rates on the coated and control materials. After the one hour scan, the animal was heparinized systemically, to stop any additional thrombogenesis, and euthanized with an intravenous injection of KCl. Each jugular vein was exposed and opened longitudinally to reveal the rod in place in the vein. After the rods were

photographed, they were removed and the thrombus was stripped, lyophilized and weighed.

Table 14.

Comparison of platelet attachment on PU modified with Compounds 6, 7.

Surface	Platelet attachment rate versus control
Uncoated PU	1.00 ± 0.43
Modified with Compounds 6, 7	0.39 ± 0.35

5

The coated PU surface performed significantly better than the uncoated surface, reducing platelet adhesion in this acute test of blood compatibility.

Example 40

Five-month Sheep Mitral Valve Implants using Modified Silicone Rubber Heart

10

Valves

Silicone rubber (SR) heart valves are modified with reagents 14, 15. The reagent is prepared at 5 mg/ml in IPA and applied, using procedures as described in Example 28, in three coats to the surface of the SR portions of a polymeric, tri-leaflet valve. The valves are sterilized using ethylene oxide and implanted in the mitral position in juvenile sheep using procedures described previously Irwin, E.D., et al, J. Invest. Surg. 6, 133-141 (1993). Three valves treated with the reagents are implanted. Valves are left in place for approximately 150 days. At the end of the implant period, the sheep are sacrificed and the hearts are explanted. The valve, including the surrounding heart tissue is removed and placed in buffered formalin. The valves are examined visually and photographed.

20

The appearance of the explanted valve leaflets should be improved by the coating. The coated valves should have minimal thrombus on the surface of the leaflets, whereas the uncoated SR valves should have substantial thrombus covering much of the surface of the leaflets. Furthermore, the thrombus present on the surface may be significantly mineralized, a further detrimental outcome that would potentially shorten the usable lifetime of the valve.

25

CLAIMS

What is claimed is:


- 5 1. A reagent for use in preparing a passivating biomaterial surface, the reagent comprising a latent reactive group and a bifunctional aliphatic acid, both groups being covalently attached to a spacer in a manner that permits the latent reactive group to be activated in order to attach the reagent to the surface, and that permits the aliphatic acid of the attached reagent to attract and bind a proteinaceous
10 moiety in order to passivate the surface.
2. A reagent according to claim 1 wherein the reagent is of the general formula $(X)_m-Y-(Z)_n$ where X is a latent reactive group, Y is a spacer radical, and Z is a bifunctional aliphatic acid, wherein m and n are, independently, ≥ 1 .
3. A reagent according to claim 2 wherein the bifunctional aliphatic acid
15 comprises an anionic region in the form of a carboxylic acid.
4. A reagent according to claim 2 wherein the bifunctional aliphatic acid comprises a fatty acid.
5. A reagent according to claim 1 wherein the proteinaceous moiety comprises albumin.
- 20 6. A reagent according to claim 1 wherein the spacer comprises a divalent spacer in order to provide a heterobifunctional reagent.
7. A reagent according to claim 1 wherein the spacer comprises a polymeric backbone in order to provide a polymeric reagent.
- 25 8. A reagent according to claim 7 wherein the polymeric backbone is selected from the group consisting of synthetic polymeric backbones selected from the group consisting of oligomers, homopolymers, and copolymers resulting from addition or condensation polymerization, and naturally occurring polymers.
9. A reagent according to claim 8 wherein the reagent is selected from the
30 group consisting of photoactivatable polyacrylamide copolymers, photoactivatable

polyvinylpyrrolidones, and photoactivatable polysiloxanes, each containing multiple pendant fatty acid groups and multiple pendant photoactivatable groups.

10. A reagent according to claim 1 wherein the spacer is selected from the group consisting of aliphatic spacers, polymeric spacers, and heteroatoms selected
5 from the group consisting of O, N, and S.


11. A reagent for use in preparing a passivating surface, the reagent selected from the group consisting of mono-2-(carboxymethyl) hexadecanamidopoly (ethylene glycol)₂₀₀ mono-4-benzoylbenzyl ether, mono-3-carboxyheptadecanamidopoly (ethylene glycol)₂₀₀ mono-4-benzoylbenzyl ether,
10 mono-2-(carboxymethyl) hexadecanamidotetra (ethylene glycol) mono-4-benzoylbenzyl ether, mono-3-carboxyhepta-decanamidotetra (ethylene glycol) mono-4-benzoylbenzyl ether, N-[2-(4-benzoylbenzyloxy) ethyl] -2-(carboxymethyl) hexadecanamide,
N-[2-(4-benzoylbenzyloxy)ethyl]-3-carboxyheptadecanamide, N-[12-(benzoylbenzyloxy) dodecyl]-2-(carboxymethyl) hexadecanamide, N-[12-(benzoylbenzyloxy) dodecyl]-3-carboxy-heptadecanamide, N-[3-(4-benzoylbenzamido) propyl]-2-(carboxymethyl) hexadecanamide, N-[3-(4-benzoylbenzamido) propyl] -3-carboxyheptadecanamide, N-(3-benzoylphenyl)-2-(carboxymethyl) hexadecanamide, N-(3-benzoylphenyl)-3-carboxyheptadecanamide,
20 N-(4-benzoylphenyl)-2-(carboxymethyl) hexadecanamide, poly(ethylene glycol)₂₀₀ mono-15-carboxypentadecyl mono-4-benzoylbenzyl ether, and mono-15-carboxypenta-decanamidopoly (ethylene glycol)₂₀₀ mono-4-benzoylbenzyl ether.

12. A reagent for use in preparing a passivating surface, the reagent selected from the group consisting of:
25 photoreactive endpoint copolymers of acrylamide and fatty acid monomers of the formula:




SUBSTITUTE SHEET (RULE 26)

photoreactive endpoint copolymers of N-vinylpyrrolidone and fatty acid monomers of the formula:




photoreactive random copolymers of N-vinylpyrrolidone and fatty acid monomers of the formula:



, and

photoreactive siloxane copolymers containing fatty acid ligands of the formula:



wherein the monomers shown in each polymer are present in random sequences and relative concentrations.

13. An intermediate for use in preparing a reagent according to claim 1, the intermediate selected from the group consisting of N-[3-Methacrylamido)propyl]-2-
5 (carboxymethyl)hexadecanamide, N-[3-Methacrylamido)propyl]-3-carboxyheptadecanamide
N-[3-(4-Benzoylbenzamido)propyl]methacrylamide, and N-(2-Mercaptoethyl)-3,5-bis(4-benzoylbenzyloxy) benzamide.

14. A method of preparing a passivating biomaterial surface, the method
10 comprising the steps of coating a biomaterial surface with a reagent according to claim 1 and activating the latent reactive group(s) under conditions suitable to covalently bond the reagent to the surface.

15. A method according to claim 14 wherein the reagent comprises a divalent spacer in order to provide a heterobifunctional reagent.

15 16. A method according to claim 14 wherein the spacer comprises a polymeric backbone in order to provide a polymeric reagent.

17. A method according to claim 14 wherein the biomaterial is selected from the group consisting of polyolefins, polystyrenes, poly(methyl)methacrylates, polyacrylonitriles, poly(vinylacetates), poly (vinyl alcohols), poly(vinyl) chlorides,
20 polyoxymethylenes, polycarbonates, polyamides, polyimides, polyurethanes, phenolics, amino-epoxy resins, polyesters, silicones, cellulose-based plastics, and rubber-like plastics.

18. A method of preparing a passivating biomaterial surface, the method comprising the steps of: (a) providing a surface derivatized with a nucleophilic
25 species, (b) reacting the surface with a reactive molecule under conditions suitable to react the reactive molecule with the nucleophilic species in order to form a bifunctional aliphatic acid attached to the surface by a covalent linkage.

19. A method according to claim 18 wherein nucleophilic species comprises an amine group and the reactive molecule comprises an anhydride group

adapted to open in the presence of the nucleophilic species and to form an amide linkage therewith.

20. A method according to claim 19 wherein the reactive molecule comprises n-tetradecylsuccinic anhydride.

5 21. A passivating biomaterial comprising a biomaterial surface having covalently attached thereto a reagent according to claim 1.

22. A surface according to claim 21 wherein the biomaterial is selected from the group consisting of polyolefins, polystyrenes, poly(methyl)methacrylates, polyacrylonitriles, poly(vinylacetates), poly (vinyl alcohols), chlorine-containing
10 polymers such as poly(vinyl) chloride, polyoxymethylenes, polycarbonates, polyamides, polyimides, polyurethanes, phenolics, amino-epoxy resins, polyesters, silicones, cellulose-based plastics, and rubber-like plastics.

23. A surface according to claim 21, the surface being positioned *in vivo* under conditions suitable to permit albumin molecules to be attracted and bound
15 thereto in order to passivate the surface.

24. A medical article fabricated from a passivating biomaterial according to claim 21.

25. A medical article according to claim 24, wherein the article comprises a blood-contacting medical device for *in vivo* application.

20 26. A passivated biomaterial surface comprising the surface of claim 23 having a proteinaceous material bound thereto.

27. A passivating biomaterial comprising a biomaterial surface having covalently attached thereto a reagent according to claim 11.

28. A surface according to claim 27 wherein the biomaterial is selected
25 from the group consisting of polyolefins, polystyrenes, poly(methyl)methacrylates, polyacrylonitriles, poly(vinylacetates), poly (vinyl alcohols), chlorine-containing polymers such as poly(vinyl) chloride, polyoxymethylenes, polycarbonates, polyamides, polyimides, polyurethanes, phenolics, amino-epoxy resins, polyesters, silicones, cellulose-based plastics, and rubber-like plastics.

29. A surface according to claim 27, the surface being positioned *in vivo* under conditions suitable to permit albumin molecules to be attracted and bound thereto in order to passivate the surface.

5 30. A medical article fabricated from a passivating biomaterial according to claim 27.

31. A medical article according to claim 30, wherein the article comprises a blood-contacting medical device for *in vivo* application.

32. A passivated biomaterial surface comprising the surface of claim 29 having a proteinaceous material bound thereto.

10 33. A passivating biomaterial comprising a biomaterial surface having covalently attached thereto a reagent according to claim 12.

34. A surface according to claim 33 wherein the biomaterial is selected from the group consisting of polyolefins, polystyrenes, poly(methyl)methacrylates, polyacrylonitriles, poly(vinylacetates), poly(vinyl alcohols), chlorine-containing
15 polymers such as poly(vinyl) chloride, polyoxymethylenes, polycarbonates, polyamides, polyimides, polyurethanes, phenolics, amino-epoxy resins, polyesters, silicones, cellulose-based plastics, and rubber-like plastics.

35. A surface according to claim 33, the surface being positioned *in vivo* under conditions suitable to permit albumin molecules to be attracted and bound
20 thereto in order to passivate the surface.

36. A medical article fabricated from a passivating biomaterial according to claim 33.

37. A medical article according to claim 36, wherein the article comprises a blood-contacting medical device for *in vivo* application.

25 38. A passivated biomaterial surface comprising the surface of claim 35 having a proteinaceous material bound thereto

39. A passivating biomaterial comprising a surface prepared according to the method of claim 18.

30 40. A surface according to claim 39 wherein the biomaterial is selected from the group consisting of polyolefins, polystyrenes, poly(methyl)methacrylates,

polyacrylonitriles, poly(vinylacetates), poly (vinyl alcohols), chlorine-containing polymers such as poly(vinyl) chloride, polyoxymethylenes, polycarbonates, polyamides, polyimides, polyurethanes, phenolics, amino-epoxy resins, polyesters, silicones, cellulose-based plastics, and rubber-like plastics.

5 41. A passivated biomaterial surface, comprising a biomaterial surface having covalently attached thereto a reagent according to claim 39, the surface being positioned *in vivo* under conditions suitable to permit albumin molecules to be attracted and bound thereto in order to passivate the surface.

 42. A medical article fabricated from a passivating biomaterial according
10 to claim 39.

 43. A medical article according to claim 42, wherein the article comprises a blood-contacting medical device for *in vivo* application.

 44. A passivated biomaterial surface comprising the surface of claim 41 having a proteinaceous material bound thereto.

THIS PAGE BLANK (USPTO)

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : A61K 47/48, A61L 27/00	A3	(11) International Publication Number: WO 99/47176 (43) International Publication Date: 23 September 1999 (23.09.99)
(21) International Application Number: PCT/US99/05245 (22) International Filing Date: 11 March 1999 (11.03.99) (30) Priority Data: 60/078,383 18 March 1998 (18.03.98) US 09/177,318 22 October 1998 (22.10.98) US (71) Applicant: SURMODICS, INC. [US/US]; 9924 West 74th Street, Eden Prairie, MN 55344 (US). (72) Inventors: GUIRE, Patrick, E.; 6741 Tartan Curve, Eden Prairie, MN 55346 (US). ANDERSON, Aron, B.; 4847 Birchwood Lane, Minnetonka, MN 55343 (US). AMOS, Richard, A.; 3437 Skycroft Circle, St. Anthony, MN 55418 (US). EVERSON, Terrence, P.; 560 Country Court, Eagan, MN 55123 (US). (74) Agents: GOLDMAN, Philip, M. et al.; Fredrikson & Byron, P.A., 1100 International Centre, 900 2nd Avenue South, Minneapolis, MN 55402-3397 (US).		(81) Designated States: AU, CA, JP, MX, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> (88) Date of publication of the international search report: 9 December 1999 (09.12.99)
(54) Title: LATENT REACTIVE BLOOD COMPATIBLE AGENTS		
(57) Abstract <p>A reagent and related method for use in passivating a biomaterial surface, the reagent including a latent reactive group and a bifunctional aliphatic acid (e.g., fatty acid), in combination with a spacer group linking the latent reactive group to the aliphatic acid in a manner that preserves the desired function of each group. Once bound to the surface, via the latent reactive group, the reagent presents the aliphatic acid to the physiological environment, <i>in vivo</i>, in a manner (e.g., concentration and orientation) sufficient to hold and orient albumin.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 99/05245

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 A61K47/48 A61L27/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 A61L A61K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 88 02623 A (BIO METRIC SYSTEMS INC) 21 April 1988 (1988-04-21) cited in the application page 8, line 27 - page 10, line 29	21-26
Y	---	1-44
X	WO 89 05616 A (BIO METRIC SYSTEMS INC) 29 June 1989 (1989-06-29) cited in the application page 11, line 8 - page 13, line 10; claims; example 2	21-26
Y	---	1-44
X	WO 97 34935 A (BSI CORP) 25 September 1997 (1997-09-25) claim 9	13
	--- -/--	



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *Z* document member of the same patent family

Date of the actual completion of the international search

8 September 1999

Date of mailing of the international search report

23.09.99

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patenilaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Seegert, K

INTERNATIONAL SEARCH REPORT

Int. Application No

PCT/US 99/05245

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
E	<p>WO 99 16907 A (SURMODICS INC) 8 April 1999 (1999-04-08) compounds III, VII, VIII table 9</p> <p>-----</p>	13, 21-32

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US 99/05245

Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☒ Claims Nos.:
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:
see FURTHER INFORMATION sheet PCT/ISA/210
3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

1. ☐ As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
- ☐ No protest accompanied the payment of additional search fees.

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

Continuation of Box I.2

Present claims 1 - 8, 10 (and independent claims referring to these claims) relate to an extremely large number of possible compounds/products. In fact, the claims contain so many options and variables that a lack of clarity within the meaning of Article 6 PCT arises to such an extent as to render a meaningful search of the claims impossible. Consequently, the search has been carried out for those parts of the application which do appear to be clear, namely claims 9, 11 - 13 (and the respective independent claims referring to these claims).

The applicant's attention is drawn to the fact that claims relating to inventions in respect of which no international search report has been established need not be the subject of an international preliminary examination (Rule 66.1(e) PCT). The applicant is advised that the EPO policy when acting as an International Preliminary Examining Authority is normally not to carry out a preliminary examination on matter which has not been searched. This is the case irrespective of whether or not the claims are amended following receipt of the search report or during any Chapter II procedure.

INTERNATIONAL SEARCH REPORT

Information on patent family members

Int. Application No

PCT/US 99/05245

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 8802623 A	21-04-1988	AT 116863 T	15-01-1995
		AU 615637 B	10-10-1991
		AU 8232087 A	06-05-1988
		CA 1305068 A	14-07-1992
		DE 3750989 D	23-02-1995
		DE 3750989 T	18-05-1995
		EP 0326579 A	09-08-1989
		JP 10179726 A	07-07-1998
		JP 2500250 T	01-02-1990
		JP 2741378 B	15-04-1998
		US 4973493 A	27-11-1990
		US 5512329 A	30-04-1996
		US 4979959 A	25-12-1990
		US 5002582 A	26-03-1991
		US 5741551 A	21-04-1998
		US 5217492 A	08-06-1993
		US 5263992 A	23-11-1993
WO 8905616 A	29-06-1989	AT 137104 T	15-05-1996
		CA 1340345 A	26-01-1999
		CA 1335721 A	30-05-1995
		DE 3855238 D	30-05-1996
		DE 3855238 T	14-11-1996
		DK 152590 A	24-08-1990
		EP 0407390 A	16-01-1991
		JP 2855223 B	10-02-1999
		JP 3503005 T	11-07-1991
		NO 180657 B	10-02-1997
		US 5512329 A	30-04-1996
		US 5002582 A	26-03-1991
		US 5741551 A	21-04-1998
		US 5258041 A	02-11-1993
WO 9734935 A	25-09-1997	AU 2431097 A	10-10-1997
		CA 2249287 A	25-09-1997
		EP 0888389 A	07-01-1999
WO 9916907 A	08-04-1999	US 5858653 A	12-01-1999
		AU 9582898 A	23-04-1999

THIS PAGE BLANK (USPTO)